

PRODUCT DATA SHEET

Sika® Unitherm® Platinum

Solvent-free, ultra high build, 2-pack, modified epoxy based intumescent fire protection coating for internally or externally exposed structural steel

PRODUCT DESCRIPTION

Sika® Unitherm® Platinum is a solvent-free, 100 % solids, 2-pack, modified epoxy based intumescent fire protection coating for internally or externally exposed structural steel, where it provides highest durability and combined corrosion protection (up to ISO 12944, corrosivity category C5) and fire protection (up to R90).

It is easily applied with standard airless spray equipment, requires no reinforcement, cures rapidly to a very tough and damage resistant finish, ready for handling and transport at the next day.

Solvent-free according to Protective Coatings Directive of German Paint Industry Association (VdL-RL 04).

USES

Sika® Unitherm® Platinum installation works to be carried out only by Sika Approved Contractors. Please observe information given by Product Data Sheets.

Sika® Unitherm® Platinum is designed primarily for in-shop application on structural steel that is to be internally or externally exposed.

No additional sealers or top coats are required unless specific lightfast coloured finishes are required.

CHARACTERISTICS / ADVANTAGES

- Solvent-free, 100 % solids
- Low odour and zero flash risk
- Halogen-free
- Easy application with single-leg spray equipment
- Can be applied in 1-coat for up to 4 mm dry film thickness, no additional reinforcement required at any time
- Application directly on blast cleaned steel surfaces
- Rapid cure - next day handling and transport
- Very tough - minimal handling damage and touch-up costs
- Highly resistant to mechanical impact and damage in service
- Suitable for small sections and complex steel sections
- Very good cosmetic appearance
- Durable for a long service life
- Expected life cycle > 25 years
- Meets Type X classification (i.e. exterior conditions), no primer and top coat needed
- Excellent corrosion protection properties according to ISO 12944, corrosivity class C5 (as coating system)
- Complies with the quality requirements (level 4) of DGNB

ENVIRONMENTAL INFORMATION

- Complies with Indoor Air Comfort Gold® limit values by EUROFINS, even as coating system

APPROVALS / STANDARDS

Independently fire tested and approved to major European and national standards including:

- EN 13381-8 (ref: ETA 20/1159)
- BS 476 parts 20-22 (ref: CF 821)
- Coating based on epoxy resin for steel protection according to EN 13501-2 and ETAG 018-2, DoP, with CE-mark

PRODUCT INFORMATION

Packaging	Sika® Unitherm® Platinum	16.8 kg and 3.7 kg net.
	Sika® Thinner E+B	25 l and 5 l
Appearance / Colour	Light grey, approx. RAL 7035	
Shelf Life	24 Months	
Storage Conditions	In originally sealed containers in a cool and dry environment.	
Density	~1.3 kg/l (± 0.1)	
Flash Point	Not applicable	
Solid Content	~100 % by volume ~100 % by weight	

TECHNICAL INFORMATION

Abrasion Resistance	~65 mg/1000 R (load: 1000g; disc: CS 10)	(ISO 5470-1)	
Compressive Strength	~45 MPa	(ISO 604)	
Tensile Strength	~10 MPa	(ISO 527-2)	
Tensile adhesion strength	Blastcleaned steel	~10 N/mm ²	(EN ISO 4624)
	Primed steel	Dependent on the primer / system	
Chemical Resistance	H ₂ SO ₄ (10%)	168 h	(EN ISO 2812-1)
	NaOH (10%)	168 h	
	Mineral Spirit	168 h	
Chemical resistance as coating system			

SYSTEM INFORMATION

Systems	<u>Approved generic primer types:</u>	
	On blast cleaned steel:	a) Without priming coat b) 2-pack epoxy, e.g. Sika® Permacor®-2706 EG c) Zinc rich epoxy, e.g. SikaCor® Zinc R d) water dispersed zinc rich epoxy, e.g. SikaCor® Zinc W e) Zinc silicate, e.g. SikaCor® Zinc ZS (+ tiecoat Sika® Permacor®-2706 EG) f) Short / medium oil alkyd, e.g. Sika® Permacor®-1705
	On manually de-rusted steel:	Sika® Permacor®-2029
	On galvanised steel:	Sika® Permacor®-2706 EG
	<u>Intumescent coating:</u>	Sika® Unitherm® Platinum
	<u>Without topcoat:</u>	a) Internal exposure b) External exposure where common epoxy behaviour or visual changes of the original colour are not an issue.

With topcoat:

If a decorative, colour resistant finish is required, then we recommend the following top coats (2-pack AY PUR):

SikaCor® EG-4
SikaCor® EG-5
SikaCor® PUR Color NEW
Sika® Permacor®-2330
Sika® Permacor®-2230 VHS

Coating System C5 (according to ISO 12944-5)

Priming: e.g. Sika® Permacor®-2706 EG
Intumescent coating: Sika® Unitherm® Platinum
Topcoat: e. g. Sika® Permacor®-2330

Decontaminable (food)
Priming: e.g. Sika® Permacor®-2706 EG
Intumescent coating: Sika® Unitherm® Platinum
Topcoat: Sika® Permacor®-2707

APPLICATION INFORMATION

Mixing Ratio	By weight	Components A : B 100 : 12
	By volume	100 : 18.4
Consumption	Theoretical material-consumption / coverage without loss for medium dry film thickness:	
	Dry film thickness	1.000 µm
	Wet film thickness	1.000 µm
	Consumption	~1.3 kg/m ²
	Coverage	~0.77 m ² /kg
Relative Air Humidity	Max. 80 %, ambient temperature shall be at least ≥ 3 K above dew point.	
Surface temperature	Substrate surface and ambient: At least + 10°C, max. + 40°C* Optimum results are achieved at temperatures over + 16°C <small>*If higher temperatures occur, please consult the Technical Department for further assistance.</small>	
Pot Life	At + 20°C	~30 min
	At + 35°C	~15 min
Curing Time	Curing and handling (at + 20°C)	
	Touch dry	~8 h
	Hard dry (ready for handling and transport)	~24 h
Waiting Time / Overcoating	Overcoating, intervals / intercoat, waiting times (at + 20°C)	
	<u>Between primer and Sika® Unitherm® Platinum:</u> After the primer reached its final drying time	
	<u>Between Sika® Unitherm® Platinum coats:</u>	
	Min.	8 h at + 20°C
Max.	Interior: 7 days at + 20°C Exterior: 2 days at + 20°C	

Between Sika® Unitherm® Platinum and SikaCor® EG-4, SikaCor® EG-5, SikaCor® PUR Color NEW, Sika® Permacor®-2330, Sika® Permacor®-2230 VHS or Sika® Permacor®-2707:

Min.	24 h at + 20°C
Max.	Interior: 7 days at + 20°C Exterior: 2 days at + 20°C

Note: The previously applied coating must be dry and free from any dirt, moisture or contaminants that could prevent or reduce adhesion (clean if necessary). If waiting times are longer than stated, then the coatings should be reactivated by suitable mechanical and / or chemical means.

Temporary storage or transport of coated steelwork must be carried out in an appropriate manner. It is 'good practise' that straps or chains must not be placed in direct contact with the coated surface.

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

Various 'info data sheets' such as processing instructions or repair instructions.
For further information please consult Sika or visit us at www.sika.de

ECOLOGY, HEALTH AND SAFETY

Local safety regulations must be observed and it advisable to wear PPI when working with this product with particular attention paid to cutting and handling.
Transportation Class: The product is not classified as hazardous good for transport. Disposal: The material is recyclable. Disposal must be according to local regulations. Please contact your local Sika sales organisation for more information.

DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

According to the EU Directive 2004/42/CE, the maximum allowed content of VOC (product category IIA / j type Sb) is 500 g/l (Limits 2010) for the ready to use product.

The maximum content of Sika® Unitherm® Platinum is < 500 g/l VOC for the ready to use product.

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

Blast cleaned steel:

Blast-cleaning to Sa 2 ½ according to ISO 8501-1. Free from dirt, oil and grease.

Steel with manual de-rusting:

Manual de-rusting (wire brushing or power tool cleaning) according to ISO 8501-1, St. 3.

Galvanized steel:

Free from dirt, oil, grease and zinc salts.

In case of permanent exposure to submersion and condensation surfaces should be sweep blasted according to ISO 12944-4.

Other surfaces:

Tests should be carried out on the specific surfaces. Please seek further information on info data sheet no. 02 'Primers for Sika® fire protection coatings'.

For contaminated and weathered surfaces e.g. galvanized or primed areas we recommend to clean with SikaCor® Wash.

MIXING

Stir component A very thoroughly using an electric mixer (start slowly, then increase up to approx. 300 rpm). Add component B carefully and mix both components very thoroughly (including sides and bottom of the container). Mix for at least 3 minutes until a homogeneous mixture is achieved. Fill mixed material into clean container and mix again shortly as described above. During mixing and handling of the materials always wear protective goggles, suitable gloves and other protective clothings.

APPLICATION

Application by airless spray will give the best results and is recommended to achieve uniform thickness and appearance. In case of application by roller or brush, additional layers may become necessary to achieve the required coating thickness, depending on type of construction, site conditions, colour shade etc. Prior to application a trial on site may be useful to ensure the selected application method will provide the requested results.

Do not thin Sika® Unitherm® Platinum!

Brushing/Rolling:

- Smaller areas

Airless spraying:

Airless spray equipment i.e. single-leg spray equipment with a flow heater, or plural component spray equipment.

- Pressure ratio: $\geq 66 : 1$
- Flow rate: ≥ 24 l/min
- Pressure rate: at least 200 bar in the spray gun
- Nozzle size 0.48 - 0.64 mm (0.019 - 0.025 inch)
- Spraying angle $20^\circ - 40^\circ$
- Material temperature:
approx. $+ 35^\circ\text{C}$ at the nozzle outlet

Helpful hints:

- Remove filter mesh
- Use direct material feed (without suction hose)
- At lower temperatures we recommend insulating the spray hose
- Max. 25 m length of spray hose
- Please adjust the spraying angles and nozzle sizes to your steel structure sizes to optimize overspray and consumption

Repairs:

To make good any misses or damage, abrade adjacent areas to a matt finish, clean off all traces of dust. Mask if necessary and then apply the Sika® Unitherm® Platinum immediately.

CLEANING OF TOOLS

Thoroughly clean tools and equipment with Sika® Thinner E+B immediately after completion or interruption of the Sika® Unitherm® Platinum application process.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local

Product Data Sheet for the exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @Sikalreland



Product Data Sheet

Sika® Unitherm® Platinum
January 2021, Version 03.01
020604000030000060

SikaUnithermPlatinum-en-IE-(01-2021)-3-1.pdf