

PRODUCT DATA SHEET

Sikaplan® SGK-15

Polymeric membrane for adhered roof waterproofing

PRODUCT DESCRIPTION

Sikaplan® SGK-15 is a multi-layer, synthetic roof waterproofing sheet based on premium-quality polyvinyl chloride (PVC) with inlay of glass non-woven and polyester fleece backing according to EN 13956.

USES

Roof waterproofing membrane for exposed flat roofs:

- Partially adhered by Sika-Trocacal® C300 & C400 adhesive.

CHARACTERISTICS / ADVANTAGES

- Resistant to permanent UV irradiation
- High dimensional stability due to glass fleece inlay
- High water vapour permeability
- Resistant to all common environmental influences
- Compatible to old bitumen due to felt backing
- Hot air welding without use of open flames
- Recyclable

APPROVALS / STANDARDS

- Polymeric sheets for roof waterproofing according to EN 13956, certified by notified body 1213-CPD-4125 and provided with the CE marking.
- Reaction to fire according to EN 13501-1.
- External fire performance tested according to ENV 1187 Brooft4 and classified according to BS:476 Part 3.
- Official Quality Approvals and Agreement Certificates and approvals.
- Monitoring and assessment by approved laboratories.
- Quality Management system in accordance with EN ISO 9001/14001.
- Production according to Responsible Care policy of Chemical Industry.

PRODUCT INFORMATION

Product Declaration	EN 13956	
Packaging	Packing unit:	see price list
	Roll length:	15.00 m
	Roll width:	2.00 m
	Roll weight:	63.00 kg
Shelf Life	Product does not expire if correctly stored.	
Storage Conditions	Rolls must be stored in a horizontal position on pallet and protected from direct sunlight, rain and snow. Do not stack pallets of rolls during transport or storage.	

Appearance / Colour	Surface:	slightly structured
	Colours:	
	Top surface:	light grey (nearest RAL 7047) lead grey (nearest RAL 7012)
	Bottom surface:	dark grey
	Top surface of sheet in other colours available on request, subject to minimum order quantities.	
Visible Defects	Pass	(EN 1850-2)
Length	15.00 m (-0 % / +5 %)	(EN 1848-2)
Width	2.00 m (-0.5 % / +1 %)	(EN 1848-2)
Effective Thickness	1.5 mm (-5 % / +10 %)	(EN 1849-2)
Straightness	≤ 30 mm	(EN 1848-2)
Flatness	≤ 10 mm	(EN 1848-2)
Mass per unit area	2.1 kg/m ² (- 5 % / + 10 %)	(EN 1849-2)

TECHNICAL INFORMATION

Resistance to Impact	hard substrate	≥ 700 mm	(EN 12691)
	soft substrate	≥ 1500 mm	
Hail Resistance	rigid substrate	≥ 22 m/s	(EN 13583)
	flexible substrate	≥ 30 m/s	
Tensile Strength	longitudinal (md) ¹⁾	≥ 600 N/50 mm	(EN 12311-2)
	transversal (cmd) ²⁾	≥ 600 N/50 mm	
	¹⁾ md = machine direction ²⁾ cmd = cross machine direction		
Elongation	longitudinal (md) ¹⁾	≥ 50 %	(EN 12311-2)
	transversal (cmd) ²⁾	≥ 50 %	
	¹⁾ md = machine direction ²⁾ cmd = cross machine direction		
Tear Strength	longitudinal (md) ¹⁾	≥ 150 N	(EN 12310-2)
	transversal (cmd) ²⁾	≥ 150 N	
	¹⁾ md = machine direction ²⁾ cmd = cross machine direction		
Joint Peel Resistance	≥ 300 N/50 mm	(EN 12316-2)	
Joint Shear Resistance	≥ 500 N/50 mm	(EN 12317-2)	
Dimensional Stability	longitudinal (md) ¹⁾	≤ 0.3 %	(EN 1107-2)
	transversal (cmd) ²⁾	≤ 0.3 %	
	¹⁾ md = machine direction ²⁾ cmd = cross machine direction		
Foldability at Low Temperature	≤ -25 °C	(EN 495-5)	
Water Tightness	Pass	(EN 1928)	

Water Vapour Transimission	$\mu = 20\ 000$	(EN 1931)
Effect of Liquid Chemicals, Including Water	On request	(EN 1847)
UV Exposure	Pass (> 5 000 h / grade 0)	(EN 1297)
External Fire Performance	$B_{ROOF}(t_4) \geq 10^\circ$ AB Flat	(EN 1187) (EN 13501-5) (BS: 476 Part 3)
Reaction to Fire	Class E	(EN ISO 11925-2, classification to EN 13501-1)

SYSTEM INFORMATION

System Structure	Ancillary products according to local price list: <ul style="list-style-type: none"> ▪ Moulded corner pieces, prefabricated corners and pipe flashings ▪ Sika-Trocal® Metal Sheet Type S ▪ Sika-Trocal® Cleaner L-100 ▪ Sika-Trocal® Welding Agent ▪ Sika-Trocal® Seam Sealant ▪ Sika-Trocal® C-300/400 (Adhesive for bonding) ▪ Sika-Trocal® C-733 (Contact adhesive)
Compatibility	The PVC compound is not compatible with direct contact to other plastics, e.g. EPS, XPS, or PF. The PVC compound is not resistant to tar, bitumen, oil and solvent containing materials.

APPLICATION INFORMATION

Ambient Air Temperature	-15 °C min. / +60 °C max. for hot air welding +5 °C min. / +60 °C max. for cold welding
Substrate Temperature	-25 °C min. / +60 °C max. for hot air welding +5 °C min. / +60 °C max. for cold welding

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

Geographical / Climate

The use of Sikaplan® SGK-15 membranes is limited to geographical locations with average monthly minimum temperatures of -25 °C. Permanent ambient temperature during use is limited to +50 °C.

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH

REGULATION (EC) NO 1907/2006 - REACH: This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product

data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w).

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The substrate surface must be uniform, smooth and free of any sharp protrusions or burrs, etc. In case of adhesion by Sika-Trocal® C-300, all layers of the built-up and substrate must be secured against wind uplift. The Polyester fleece laminated to Sikaplan® SGK-15 underside separates sufficiently from any incompatible substrate. It prevents from direct contact to bitumen or plastic material, e.g. expanded polystyrene (EPS), extruded polystyrene (XPS), polyurethane (PUR), polyisocyanurate (PIR) or phenolic foam (PF) for compatibility in the built-up.

APPLICATION

Installation works must be carried out only by Licensed Sika-Trocac Roofing Contractors.
Installation of some ancillary products, e.g. contact adhesives/thinners is limited to temperatures above +5 °C. Please refer to the respective Product Data Sheets.
Special measures may be compulsory for installation below +5 °C ambient temperature due to safety requirements in accordance with national regulations.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @Sikalreland



Product Data Sheet

Sikaplan® SGK-15
June 2022, Version 03.01
020905051000151101

SikaplanSGK-15-en-IE-(06-2022)-3-1.pdf