

PRODUCT DATA SHEET

SikaShield® E74 PE SA 3 mm

3 mm elastomeric self-adhesive bituminous underlay membrane flexible at -25 °C

PRODUCT DESCRIPTION

SikaShield® E74 PE SA 3 mm is an SBS modified, self-adhesive bituminous membrane. It is reinforced with a non-woven polyester fabric dimensionally stabilised with glass fibre and is flexible at -25 °C. The top surface is coated with a polyethylene foil. The underside has a removable liner over the self adhesive compound for easy application.

USES

The Product is used as a base sheet in multi-layer systems for:

- Flat and pitched roofs
- New construction and refurbishment projects
- Inverted Roofs
- As a base sheet in multi-layer systems

PRODUCT INFORMATION

Chemical Base	Composition	SBS modified bitumen	
	Reinforcing material	non-woven polyester fabric dimensionally stabilised with glass fibre	
Packaging	Roll width	1.0 m	(EN 1848-1)
	Roll length	8.0 m	
Shelf Life	12 months from date of production		
Storage Conditions	The Product must be stored in original unopened and undamaged packaging in dry conditions and temperatures between +5 °C and +35 °C. Store in a vertical position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.		
Appearance / Colour	Top surface	Polyethylene film	
	Bottom surface	Removable foil	
Effective Thickness	Effective thickness	3.0 mm ± 0.2 mm	(EN 1849-1)

TECHNICAL INFORMATION

Maximum tensile force	Longitudinal (MD)	400 N/50 mm ± 80 N/50 mm	(EN 12311-1)
	Transversal (CMD)	300 N/50 mm ± 60 N/50 mm	
Elongation at maximum tensile force	Longitudinal (MD)	35 % ± 15 %	(EN 12311-1)
	Transversal (CMD)	40 % ± 15 %	
Resistance to Tearing (nail shank)	Longitudinal (MD)	140 N ± 42 N	(EN 12310-1)
	Transversal (CMD)	140 N ± 42 N	
Joint Shear Resistance	Longitudinal	350 N/50 mm ± 70 N/50 mm	(EN 12317-1)
	Transversal	250 N/50 mm ± 50 N/50 mm	
Flexibility at low temperature	≤ -25 °C		(EN 1109)
Water Tightness	Method B: 24 hours at 60 kPa	Pass	(EN 1928)
Permeability to Water Vapour	μ = 100'000		(EN 1931)
UV Exposure	SikaShield® E74 PE SA 3 mm must be protected from damage during any ongoing site activities. The membrane can only be used as temporary waterproofing for 2 weeks before installation of a suitable cap sheet is required.		
Reaction to Fire	Class E		(EN 13501-1)

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH: This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w).

APPLICATION INSTRUCTIONS

Please refer to the SikaShield Installation Guide.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @Sikalreland



Product Data Sheet
SikaShield® E74 PE SA 3 mm
December 2022, Version 02.01
02092001198000092

SikaShieldE74PESA3mm-en-IE-(12-2022)-2-1.pdf

