

# PRODUCT DATA SHEET

## Primer-600

PRIMER FOR SARNAVAP®-5000 E SA / SIKAPLAN® RV-S / SARNAFIL® TG 76 FSA / SARNAFIL® G 410 FSA

### PRODUCT DESCRIPTION

Primer-600 is a synthetic rubber and resin based 1-part ready to use primer for improving the adhesion properties of specific Sika® roof membranes.

### USES

A primer for applying self-adhesive technologies onto various substrates

- SARNAVAP®-5000 E SA
- Sikaplan® RV-s
- Sarnafil® TG 76 FSA
- Sarnafil® G 410- FSA

A primer for Sika® Trocal C-300 to critical substrates.

### CHARACTERISTICS / ADVANTAGES

- Proven performance over decades
- Easily applied
- Flame free application
- High adhesion to different structural deck types and substrates
- 1-part ready to use
- Increased adhesion for the specific membrane types
- Applied by brush or roller

### PRODUCT INFORMATION

<b>Chemical Base</b>	Synthetic rubber and synthetic resins based primer. Contains solvents.
<b>Packaging</b>	5 kg or 12,5 kg Containers. Packing unit: Euro pallet or single container. Refer to current price list for packaging variations.
<b>Appearance / Colour</b>	Black
<b>Shelf Life</b>	12 months from date of production
<b>Storage Conditions</b>	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.
<b>Density</b>	~0,84 kg/l (+20 °C)
<b>Volatile organic compound (VOC) content</b>	VOC-CH 63,4 % VOC-EU 63,4 %
<b>Consistency</b>	Liquid

### APPLICATION INFORMATION

<b>Consumption</b>	~150–500 g/m <sup>2</sup> Consumption depends on the roughness and absorbency of the substrate. These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.
<b>Ambient Air Temperature</b>	+5 °C min
<b>Substrate Temperature</b>	+5 °C min
<b>Setting Time</b>	Final properties are achieved after ~1 week, depending on temperature and humidity.
<b>Tack Free Time</b>	~30 minutes Depending on environmental conditions, characteristics of the substrate and amount of primer applied
<b>Waiting Time / Overcoating</b>	~30 minutes Depending on environmental conditions, characteristics of the substrate and amount of primer applied

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

The substrate surface/supporting layer must be of sufficient structural adequacy to apply the new roof membrane and all layers of the roof build-up including wind uplift.

The substrate can be one of the following materials: Concrete, lightweight concrete, screed, brick, plaster, Oriented Strand Boards (OSB), plywood panels, timber boards, metal decking.

### SUBSTRATE PREPARATION

The substrate must be uniform, firm, solvent resistant, smooth and free of any sharp protrusion or burrs, clean, dry, free of grease, bitumen, oil, paint coatings and dust. If heavily contaminated or oiled, sheet metal decking must be cleaned with cleaner before applying the primer.

### MIXING

1-part ready to use and must not be thinned or mixed with other products. Before use, stir product thoroughly.

### APPLICATION

Application must be during dry weather at temperatures above +5 °C.

Apply a uniform, thin coat of Primer-600 to the substrate by brush or roller. Allow primer to dry tack free. Apply roofing membrane on the same day. Absorbent substrates may require two coats. Allow sufficient overcoating time for 2<sup>nd</sup> coat.

### CLEANING OF TOOLS

Clean all tools and application equipment with cleaner immediately after use. Hardened material can only be mechanically removed.

## LIMITATIONS

- Do not apply to wet, damp or unclean surfaces.
- Do not use on the following substrates: Synthetic membranes e.g. PVC, FPO.
- Do not use on EPS/XPS thermal insulation boards.
- Do not use on existing coated surfaces.

## VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

## ECOLOGY, HEALTH AND SAFETY

Local safety regulations must be observed and it advisable to wear PPI when working with this product with particular attention paid to cutting and handling. Transportation Class: The product is not classified as hazardous good for transport. Disposal: The material is recyclable. Disposal must be according to local regulations. Please contact your local Sika sales organisation for more information.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either

from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**SIKA IRELAND LIMITED**

Ballymun Industrial Estate  
Ballymun  
Dublin 11, Ireland  
Tel: +353 1 862 0709  
Web: [www.sika.ie](http://www.sika.ie)  
Twitter: @Sikalreland



Product Data Sheet  
Primer-600  
June 2019, Version 02.01  
020945072100000004

Primer-600-en-IE-(06-2019)-2-1.pdf

