

PRODUCT DATA SHEET

EVERBUILD STICK2® Contact Adhesive

GENERAL ALL PURPOSE CONTACT ADHESIVE FOR USE WITH A WIDE VARIETY OF MATERIALS

PRODUCT DESCRIPTION

EVERBUILD STICK2® Contact Adhesive is a premium grade rubber-based contact adhesive suitable for use with a wide variety of materials for both professional and DIY use. The product may be used internally and externally for bonding decorative laminates, all types of wood, rigid PVC, ABS, cork, linoleum, rubber, stone, metals and dense fabrics.

USES

- Laminate materials
- Bonding PU foam or mineral wool panels to plaster-board.
- Bonding metals to most surfaces.
- Bonds wood, rubber, most plastics and leather, cork, lino, rigid PVC.

PRODUCT INFORMATION

Packaging	125 ml, 250 ml, 750 ml, 5 ltr and 500 ml Spray
Colour	Beige
Shelf Life	12 months from date of manufacture in original unopened containers.
Storage Conditions	Store in original unopened containers between 5 °C and 25 °C away from sources of ignition.
Density	ca.0.86 g/cm ³ at 20 °C
Viscosity	4500 +/- 1000 cP (much lower for spray)

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

The surfaces to be glued should be clean and free from dust, grease and other contaminants. Materials should be stored in a warm environment prior to bonding to avoid chilling of the glue line, which leads

CHARACTERISTICS / ADVANTAGES

- Excellent adhesion - adheres to most common surfaces.
- Exceptional bond strength - out performs conventional wood glues.
- Internal and external use (excluding 5ltr size) - excellent weathering and aging properties.

Base	Polychloroprene
Solids	25 +/- 2 %
Coverage	2.5 m ² / litre (4-8 m ² Spray)
Tack Life	5 – 30 minutes (2-5 minutes spray)

to extended setting times and possible adhesion problems.

APPLICATION METHOD / TOOLS

Tube / Tin

Stir adhesive well before use. DO NOT USE BELOW 10 °C.

The adhesive is applied to both surfaces in a thin coat

using a short stiff brush or spreader. Allow the surfaces to become "touch dry" (adhesive is glossy and no longer transfers to the knuckles) for between 10 and 20 minutes. Porous surfaces must receive two coats, allowing the adhesive to dry between coats. Align the bond edges and bond under maximum pressure. For best results, laminates should be nip-rolled or pressed. If this is not possible, use a hard roller and go over the entire surface using as much bodyweight as possible, working from the centre outwards. Seams and edges should also receive extra pressure.

Spray

Shake the can well before use.

Select the fan width by turning the nozzle to the desired position. Spray adhesive from 6-8 inches away onto one or both surfaces, depending on the type of surface/strength of bond required.

The surfaces to be glued should be clean and free from dust, grease and other contaminants. Shake well before use. Select fan width by turning to desired setting. Spray adhesive from 15 to 20 cm (6 to 8 inches approx.) away onto one or both surfaces, depending on type of strength of bond required.

STRONG BONDING

Apply 1-3 coats (depending on strength required) to both surfaces. Allow solvent to evaporate (30 seconds) and press surfaces together from centre outwards.

TEMPORARY REPOSITIONABLE BONDING

Spray on one surface only and allow to dry for 2-3 minutes before bonding. Excess adhesive can be removed with STICK 2® CONTACT ADHESIVE THINNER AND CLEANER. To prevent spray nozzle from blocking: at the end of each day turn can upside down and press nozzle until spray is clear of adhesive.

Excess adhesive can be removed using EVERBUILD® FOAM CLEANER. To prevent spray nozzle from blocking: at the end of each use, turn can upside down and press nozzle until spray is clear of adhesive.

The newly bonded material should not be subjected to extreme temperature changes for 3 to 4 days after bonding. Avoid further fabrication until the adhesive has fully cured.

LIMITATIONS

- Do not use on soft (plasticised) PVC.
- Do not use on polystyrene.
- Do not use on bitumen, asphalt or cellulose-painted surfaces.
- Do not use on bitumen- or tar-leaching products.
- Do not use as a mirror adhesive as the product may attack the mirror backing.
- Do not expose bonded areas to direct sunlight for three days after fixing.
- Do not use in areas subject to continuous water im-

mersion.

- Always allow the adhesive to become touch dry on both surfaces before bringing surfaces together – premature bonding will cause solvent entrapment and blistering of laminates.
- At low temperatures, care must be taken to ensure that the temperature of the adhesive and of both surfaces to be bonded is higher than the ambient temperature. Cold materials have a strong tendency to attract moisture present in the surrounding air, which can have a disastrous effect on the bond strength.

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

Consult MSDS for full list of hazards.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @Sikalreland



Product Data Sheet
EVERBUILD STICK2® Contact Adhesive
March 2020, Version 03.01
020204030050000001

EVERBUILDSTICK2ContactAdhesive-en-IE-(03-2020)-3-1.pdf

