

BUILDING TRUST

SYSTEM DATA SHEET Sikafloor[®] MultiDur EB-24

BROADCAST UNICOLOUR EPOXY FLOOR COVERING WITH HIGH MECHANICAL RESISTANCE

PRODUCT DESCRIPTION

Sikafloor[®] MultiDur EB-24 is a slip resistant, coloured, epoxy covering with high mechanical resistance for flooring applications

USES

Sikafloor[®] MultiDur EB-24 installation works to be carried out only by Sika Approved Contractors. Please observe information given by Product Data Sheets.

- for concrete and cement screeds with normal up to medium heavy wear e.g. storage and assembly halls, maintenance workshops, garages and loading ramps.
- for multi-storey and underground car parks and for wet process areas, e.g. beverage and food industry

CHARACTERISTICS / ADVANTAGES

- High wear resistance
- High mechanical resistance
- Good chemical resistance
- Easy application
- Waterproof
- Gloss finish
- Slip resistant

APPROVALS / STANDARDS

 Fire classification test, Bfl-S1 according to DIN EN 13501-1, Report No.2007-B-0181/15, Germany, July 2007

System Data Sheet Sikafloor® MultiDur EB-24 November 2019, Version 04.01 02081190000000017

SYSTEM INFORMATION

System Structure		
		321
	Sikafloor® MultiDur EB-24 system (^	′ 2–4 mm)
	<u>1. Primer</u>	Sikafloor [®] -156/-161
	2. Wearing coat & broadcast in ex-	Sikafloor [®] -263 SL or
	cess	Sikafloor [®] -264
		broadcast with quartz sand in excess
	3. Top coat	Sikafloor [®] -264
Composition	Ероху	
Appearance	Slip resistant, gloss finish	
Colour	Available in various colour shades.	
Nominal Thickness	~2.0–4.0 mm	
TECHNICAL INFORMATION		
Reaction to Fire	Bfl-S1	(DIN EN 13501-1)

Refer to the chemical resistan		
	Refer to the chemical resistance of Sikafloor®-264	
Exposure*	Dry heat	
Permanent	+50 °C	
Short-term max. 7 d	+80 °C	
Short-term max. 12 h	+100 °C	
Short-term moist/wet heat* up to +80 °C where exposure is only occasion- al (i.e. during steam cleaning etc.) *No simultaneous chemical and mechanical exposure.		
R11 V4 (Quartz Sand 0.3-0.8 r	nm) (DIN 51130)	
R12 V6 (Quartz Sand 0.6-1.2 r	mm) (DIN 51130)	
	Exposure* Permanent Short-term max. 7 d Short-term max. 12 h Short-term moist/wet heat* u al (i.e. during steam cleaning o	



System Data Sheet Sikafloor® MultiDur EB-24 November 2019, Version 04.01 02081190000000017

APPLICATION INFORMATION

Sikafloor [®] MultiDur	Sikafloor® MultiDur EB-24 system (~ 2–4mm)			
Coating System	Product	Consumption		
Primer				
Wearing coat	Sikafloor [®] -263 SL	~ 4 kg /m² (2 kg/m²		
		binder + 2 kg/m² quartz		
	1:1 with quartz sand	sand)		
	0.06–0.3mm	<u> </u>		
Broadcast in excess	quartz sand 0.3 – 0.8 mm	~ 4–6 kg/m²		
Top coat	1–2 × Sikafloor [®] -264	~0.6–0.8 kg/m²		
Please refer to the i	Please refer to the individual Product Data Sheet			
+10 °C min. / +30 °C	+10 °C min. / +30 °C max.			
80 % r.h. max.	80 % r.h. max.			
Beware of condensa	Beware of condensation!			
	The substrate and uncured floor must be at least 3 °C above dew point to			
reduce the risk of co	reduce the risk of condensation or blooming on the floor finish.			
+10 °C min. / +30 °C	+10 °C min. / +30 °C max.			
When performing a	When performing application work with Sikafloor® MultiDur EB-24, the			
	substrate moisture content must not exceed 4 % pbw measured by			
	Tramex.			
Tramex.		p		
	Tramex meter, CM - measure			
Test method: Sika [®] - od.		ment or Oven-dry-meth-		
Test method: Sika®- od. No rising moisture a	Tramex meter, CM - measure	ment or Oven-dry-meth-		
Test method: Sika®- od. No rising moisture a Before applying Sika	Tramex meter, CM - measure according to ASTM (Polyethyle afloor®–263 SL /-264 on Sikafl	ment or Oven-dry-meth-		
Test method: Sika®- od. No rising moisture a Before applying Sika Substrate temperat	Tramex meter, CM - measure according to ASTM (Polyethyle afloor®–263 SL /-264 on Sikafl ure Minimum	ment or Oven-dry-meth- me-sheet). oor®-156/161 allow: Maximum		
Test method: Sika®- od. No rising moisture a Before applying Sika	Tramex meter, CM - measure according to ASTM (Polyethyle afloor®–263 SL /-264 on Sikafl	ment or Oven-dry-meth- ene-sheet). oor®-156/161 allow: Maximum 3 days		
Test method: Sika®- od. No rising moisture a Before applying Sika <u>Substrate temperat</u> +10 °C	Tramex meter, CM - measure according to ASTM (Polyethyle afloor®–263 SL /-264 on Sikafl ure Minimum 24 hours	ment or Oven-dry-meth- me-sheet). oor®-156/161 allow: Maximum		
Test method: Sika®- od. No rising moisture a Before applying Sika Substrate temperat +10 °C +20 °C +30 °C	Tramex meter, CM - measure according to ASTM (Polyethyle afloor®–263 SL /-264 on Sikafl ure <u>Minimum</u> 24 hours 12 hours 8 hours	ment or Oven-dry-meth- ene-sheet). oor®-156/161 allow: Maximum 3 days 2 days 1 day		
Test method: Sika®- od. No rising moisture a Before applying Sika <u>Substrate temperat</u> +10 °C +20 °C +30 °C Before applying Sika	Tramex meter, CM - measure according to ASTM (Polyethyle afloor®–263 SL /-264 on Sikafl ure Minimum 24 hours 12 hours 8 hours afloor®–264 on Sikafloor®–263	ment or Oven-dry-meth- ene-sheet). oor®-156/161 allow: <u>Maximum</u> <u>3 days</u> <u>2 days</u> <u>1 day</u> <u>3 SL /-264 allow:</u>		
Test method: Sika®- od. No rising moisture a Before applying Sika Substrate temperat +10 °C +20 °C +30 °C Before applying Sika Substrate temperat	Tramex meter, CM - measure according to ASTM (Polyethyle afloor®–263 SL /-264 on Sikafl ure <u>Minimum</u> 24 hours 12 hours 8 hours afloor®–264 on Sikafloor®–263 ure <u>Minimum</u>	ment or Oven-dry-meth- ene-sheet). oor®-156/161 allow: <u>Maximum</u> 3 days 2 days 1 day 3 SL /-264 allow: Maximum		
Test method: Sika®- od. No rising moisture a Before applying Sika Substrate temperat +10 °C +20 °C +30 °C Before applying Sika Substrate temperat +10 °C	Tramex meter, CM - measure according to ASTM (Polyethyle afloor®–263 SL /-264 on Sikafl ure Minimum 24 hours 12 hours 8 hours afloor®–264 on Sikafloor®–263 ure Minimum 30 hours	ment or Oven-dry-meth- ene-sheet). oor®-156/161 allow: <u>Maximum</u> <u>3 days</u> <u>2 days</u> <u>1 day</u> 3 SL /-264 allow: <u>Maximum</u> <u>48 hours</u>		
Test method: Sika®- od. No rising moisture a Before applying Sika Substrate temperat +10 °C +20 °C +30 °C Before applying Sika Substrate temperat +10 °C +20 °C	Tramex meter, CM - measure according to ASTM (Polyethyle afloor®–263 SL /-264 on Sikafl ure Minimum 24 hours 12 hours 8 hours afloor®–264 on Sikafloor®–263 ure Minimum 30 hours 24 hours	ment or Oven-dry-meth- ene-sheet). 000r®-156/161 allow: <u>Maximum</u> <u>3 days</u> <u>2 days</u> <u>1 day</u> 3 SL /-264 allow: <u>Maximum</u> <u>48 hours</u> 24 hours		
Test method: Sika®- od. No rising moisture a Before applying Sika Substrate temperat +10 °C +20 °C +30 °C Before applying Sika Substrate temperat +10 °C +20 °C +30 °C	Tramex meter, CM - measure according to ASTM (Polyethyle afloor®–263 SL /-264 on Sikafl ure Minimum 24 hours 12 hours 8 hours afloor®–264 on Sikafloor®–265 ure Minimum 30 hours 24 hours 16 hours	ment or Oven-dry-meth- ene-sheet). oor®-156/161 allow: <u>Maximum</u> 3 days 2 days 1 day 3 SL /-264 allow: <u>Maximum</u> 48 hours 24 hours 30 hours		
Test method: Sika®- od. No rising moisture a Before applying Sika Substrate temperat +10 °C +20 °C +30 °C Before applying Sika Substrate temperat +10 °C +20 °C +30 °C Times are approxim	Tramex meter, CM - measure according to ASTM (Polyethyle afloor®–263 SL /-264 on Sikafl ure Minimum 24 hours 12 hours 8 hours afloor®–264 on Sikafloor®–263 ure Minimum 30 hours 24 hours 16 hours ate and will be affected by ch	ment or Oven-dry-meth- ene-sheet). oor®-156/161 allow: <u>Maximum</u> <u>3 days</u> <u>2 days</u> <u>1 day</u> 3 SL /-264 allow: <u>Maximum</u> <u>48 hours</u> <u>24 hours</u> <u>30 hours</u> anging ambient condi-		
Test method: Sika®- od. No rising moisture a Before applying Sika Substrate temperat +10 °C +20 °C +30 °C Before applying Sika Substrate temperat +10 °C +20 °C +30 °C Times are approxim tions particularly te	Tramex meter, CM - measure according to ASTM (Polyethyle afloor®–263 SL /-264 on Sikafl ue Minimum 24 hours 12 hours 8 hours afloor®–264 on Sikafloor®–265 ure Minimum 30 hours 24 hours 16 hours ate and will be affected by ch mperature and relative humic	ment or Oven-dry-meth- ene-sheet). oor®-156/161 allow:		
Test method: Sika®- od. No rising moisture a Before applying Sika <u>Substrate temperat</u> +10 °C +20 °C +30 °C Before applying Sika <u>Substrate temperat</u> +10 °C +20 °C +30 °C Times are approxim tions particularly te	Tramex meter, CM - measure according to ASTM (Polyethyle afloor®–263 SL /-264 on Sikafl ure Minimum 24 hours 12 hours 8 hours afloor®–264 on Sikafloor®–265 ure Minimum 30 hours 24 hours 16 hours ate and will be affected by ch mperature and relative humic Foot traffic Light traffic	ment or Oven-dry-meth- ene-sheet). oor®-156/161 allow: <u>Maximum</u> <u>3 days</u> <u>2 days</u> <u>1 day</u> 3 SL /-264 allow: <u>Maximum</u> <u>48 hours</u> <u>24 hours</u> <u>30 hours</u> anging ambient condi- lity <u>Full cure</u>		
Test method: Sika®- od. No rising moisture a Before applying Sika Substrate temperat +10 °C +20 °C +30 °C Before applying Sika Substrate temperat +10 °C +20 °C +30 °C Times are approxim tions particularly te Temperature f +10 °C	Tramex meter, CM - measure according to ASTM (Polyethyle afloor®–263 SL /-264 on Sikafl ue Minimum 24 hours 12 hours 8 hours afloor®–264 on Sikafloor®–265 ure Minimum 30 hours 24 hours 16 hours ate and will be affected by ch mperature and relative humic	ment or Oven-dry-meth- ene-sheet). oor®-156/161 allow:		
	Coating System Primer Wearing coat Broadcast in excess Top coat Please refer to the i +10 °C min. / +30 °C 80 % r.h. max. Beware of condensa The substrate and u reduce the risk of co +10 °C min. / +30 °C	Coating SystemProductPrimer1 x Sikafloor®-156 /-161Wearing coatSikafloor®-263 SL or Sikafloor®-264 filled 1:1 with quartz sand 0.06-0.3mmBroadcast in excessquartz sand 0.3 - 0.8 mmTop coat1-2 × Sikafloor®-264Please refer to the individual Product Data Sheet +10 °C min. / +30 °C max.80 % r.h. max.Beware of condensation! The substrate and uncured floor must be at least reduce the risk of condensation or blooming on the +10 °C min. / +30 °C max.When performing application work with Sikafloor		

PRODUCT INFORMATION

Packaging	Please refer to the individual Product Data Sheet	
Shelf Life	Please refer to the individual Product Data Sheet	
Storage Conditions	Please refer to the individual Product Data Sheet	

System Data Sheet Sikafloor® MultiDur EB-24 November 2019, Version 04.01 02081190000000017



MAINTENANCE

CLEANING

Please refer to the Information Manual Sikafloor®-Cleaning Regime

FURTHER DOCUMENTS

Please refer to :

- Sika[®] Information Manual Mixing & Applications of Flooring systems
- Sika[®] Information Manual Evaluation and Preparation of Surfaces for Flooring systems

LIMITATIONS

- Do not apply Sikafloor[®] MultiDur EB-24 on substrates with rising moisture.
- Freshly applied Sikafloor[®] MultiDur EB-24 must be protected from damp, condensation and water for at least 24 hours.
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.
- For exact colour matching, ensure the Sikafloor[®]-264 in each area is applied from the same control batch numbers.
- Under certain conditions, underfloor heating or high ambient temperatures combined with high point loading, may lead to imprints in the resin.
- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

Local safety regulations must be observed and it advisable to wear PPI when working with this product with particular attention paid to cutting and handling. Transportation Class: The product is not classified as hazardous good for transport. Disposal: The material is recyclable. Disposal must be according to local regulations. Please contact your local Sika sales organisation for more information.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information. or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA IRELAND LIMITED

Ballymun Industrial Estate Ballymun Dublin 11, Ireland Tel: +353 1 862 0709 Web: www.sika.ie Twitter: @SikaIreland



System Data Sheet Sikafloor® MultiDur EB-24 November 2019, Version 04.01 02081190000000017 SikafloorMultiDurEB-24-en-IE-(11-2019)-4-1.pdf

