

PRODUCT DATA SHEET

Sikalastic®-601 BC

PRODUCT DESCRIPTION

Sikalastic®-601 BC is a one-component, cold-applied, seamless, highly elastic, moisture-triggered polyurethane Base Coat (BC) designed to provide easy application and a durable solution as part of the SikaRoof® MTC systems.

USES

Sikalastic®-601 BC installation works to be carried out only by Sika Approved Contractors. Please observe information given by Product Data Sheets.

- Base Coat for SikaRoof® MTC 12,15, 18, 22 in both new construction and refurbishment projects
- For cold and warm roof build-ups
- For roofs displaying complex detail areas, even when accessibility is limited
- For cost efficient life cycle extension of failing roofs
- Base Coat for Sika SolaRoof® MTC 12, 15, 18, 22 in combination with Sikalastic®-621 SR as highly reflective roof waterproofing system for excellent cool roof characteristics and photovoltaic panels.

CHARACTERISTICS / ADVANTAGES

- Proven technology - over 25 year track record
- One component – no mixing, easy and ready to use
- Cold applied - requires no heat or flame
- Seamless roof waterproofing membrane
- Compatible with Sika® Reemat Premium - easy to detail
- Fast curing - free from rain damage almost immediately on application
- High elastic and crack-bridging - retains flexibility even at low temperatures
- High root resistance
- Easily recoated when needed - no stripping required
- Good adhesion to most substrates- see primer chart
- Vapour permeable - allows substrate to breathe
- Strong resistance to common atmospheric chemicals

APPROVALS / STANDARDS

As part of SikaRoof® MTC Systems
Liquid applied roof waterproofing kit according to ETAG 005, ETA-09/0139 issued by technical assessment body British Board of Agrément (BBA), provided with the CE marking. Declaration of Performance:

- SikaRoof® MTC 12: 44125185
 - SikaRoof® MTC 15: 27265077
 - SikaRoof® MTC 18: 15813688
 - SikaRoof® MTC 22: 75346978
- Root resistance approval according FLL (Institute of Horticulture)
 - Reaction to fire according to EN 13501-1: Euroclass E
 - External fire performance according to EN 13501-5:
 - BRoof (t1) - BRoof (t4) (SikaRoof® MTC 15, non-combustible substrates)
 - BRoof (t1)- BRoof (t4) (SikaRoof® MTC 18, build up roofs)
 - BRoof (t1) (SikaRoof® MTC 22, Build up roofs)

PRODUCT INFORMATION

Chemical Base	One-component, moisture-triggered aliphatic Polyurethane	
Packaging	5 l (~6.8 kg) metal pail 15 l (~20.4 kg) metal pail	
Colour	Oxide red (RAL 3011)	
Shelf Life	9 months from date of production	
Storage Conditions	The product must be stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between 0 °C and +25 °C. Higher storage temperatures may reduce shelf life of product. Reference shall also be made to the storage recommendations within the safety data sheet.	
Density	~1.36 kg/l (+23 °C)	(EN ISO 2811-1)
Solid content by weight	~84 % (+23 °C / 50 % r.h.)	
Solid content by volume	~78 % (+23 °C / 50 % r.h.)	

TECHNICAL INFORMATION

Chemical Resistance	Salt spray	1000 hours continuous exposure	(ASTM B117)
	Prohesion testing	1000 hours cyclic exposure	(ASTM G85-94: Annex A5)
Strong resistance to a wide range of reagents including paraffin, petrol, fuel oil, white spirit, acid rain, detergents and moderate solutions of acids and alkalis. Some low molecular weight alcohols can soften the material. Contact Sika technical service for specific information.			
Service Temperature	-30 °C min. / + 80 °C max.		

SYSTEM INFORMATION

System Structure	Please refer to System Data Sheets of SikaRoof® MTC Systems
System Performance	Please refer to System Data Sheets of SikaRoof® MTC Systems

APPLICATION INFORMATION

Ambient Air Temperature	+5 °C min. / +35 °C max.
Relative Air Humidity	5 % r.h. min. / 85 % r.h. max.
Substrate Temperature	+5 °C min. / +60 °C max. ≥3 °C above dew point
Substrate Moisture Content	≤4 % pbw moisture content. Test method: Sika®-Tramex meter No rising moisture according to ASTM (Polyethylene-sheet).
Substrate Pre-Treatment	Please refer to System Data Sheets of SikaRoof® MTC Systems
Pot Life	Sikalastic®-601 BC is designed for fast curing. High temperatures combined with high air humidity will accelerate the curing process. Thus, material in opened containers should be applied immediately. In opened containers, the material will form a film after 1 hour approx. (+20 °C / 50 % r.h.).

Waiting Time / Overcoating

Ambient conditions

+5 °C / 50 % r.h.

+10 °C / 50 % r.h.

+20 °C / 50 % r.h.

Minimum waiting time*

18 hours

8 hours

6 hours

*After four days the surface must be cleaned and primed with Sika® Reactivation Primer before continuing.

Note: Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

Applied Product Ready for Use

Please refer to System Data Sheets of SikaRoof® MTC Systems

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

The surface must be sound, of sufficient strength, clean, dry and free of dirt, oil, grease and other contamination. Depending on the material the substrate must be primed or mechanically cleaned. Grinding may be necessary to level the surface. Suitable substrates are such as: concrete, bituminous felts and coatings, metal, brickwork, asbestos cement, ceramic tiles, wooden substrates.

For detailed information regarding substrate preparation and primer chart please refer to Method Statement No. 850 94 01 "SikaRoof® MTC Systems".

MIXING

Mixing is not required, however if the product is settled or separated on opening, stir Sikalastic®-601 BC gently but thoroughly in order to achieve a uniform colour. Stirring gently will minimise air entrainment.

APPLICATION

Prior the application of Sikalastic®-601 BC the priming coat if used must have cured tack-free. For the Waiting Time / Overcoating please refer to the PDS of the appropriate primer. Damageable areas (handrails etc.) have to be protected with tape or plastic wrapping. Please note, always begin with details prior to the installation of the horizontal surface.

1. Apply first coat of Sikalastic®-601 BC. Work only so far in advance that the material stays liquid*.
2. Roll in the Sikalastic® Reemat. Overlap the Reemat a minimum 5 cm and ensure overlaps are sufficiently wet to bond both layers.
3. The roller may require only a little extra material to keep wetted but no further significant material needs to be added at this stage.
4. After the coat is dry enough to walk on, seal the roof area with second coat of Sikalastic® 621.
5. For SikaRoof MTC 22 apply a third coat of Sikalastic® 621

CLEANING OF TOOLS

Clean all tools and application equipment with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

FURTHER DOCUMENTS

For detailed information regarding substrate prepara-

tion, primer chart and application method please refer to Method Statement of SikaRoof® MTC Systems No. 850 94 01.

LIMITATIONS

- Do not apply Sikalastic®-601 BC on substrates with rising moisture.
- Sikalastic®-601 BC is not suitable for permanent water immersion.
- On substrates likely to exhibit outgassing, apply during falling ambient and substrate temperature. If applied during rising temperatures "pin holing" may occur from rising air.
- Do not dilute Sikalastic®-601 BC with any solvent.
- Do not use Sikalastic®-601 BC for indoor applications.
- Do not apply close to the air intake vent of a running air conditioning unit.
- Do not apply Sikalastic®-601 BC directly on Sikalastic® Insulation boards. Instead use Sikalastic® Carrier between Sikalastic® Insulation board and Sikalastic®-601 BC.
- Volatile bituminous materials may stain and or soften below the coating.
- Areas with high movement, irregular substrates, or timber based roof decks require a complete layer of Sikalastic® Carrier.
- Do not apply cementitious products (e.g. tile mortar) directly onto Sikalastic®-601 BC.

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

Local safety regulations must be observed and it advisable to wear PPI when working with this product with particular attention paid to cutting and handling. Transportation Class: The product is not classified as hazardous good for transport. Disposal: The material is recyclable. Disposal must be according to local regulations. Please contact your local Sika sales organisation for more information.

DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

According to the EU-Directive 2004/42/CE, the maximum allowed content of VOC (Product category IIA / i type sb) is 500 g/l (Limits 2010) for the ready to use product.

The maximum content of Sikalastic®-601 BC is <500 g/l VOC for the ready to use product.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @Sikalreland



Product Data Sheet
Sikalastic®-601 BC
August 2019, Version 02.01
020915205000000005

Sikalastic-601BC-en-IE-(08-2019)-2-1.pdf