

SYSTEM DATA SHEET

Sika Comfortfloor® PS-66

SEAMLESS, SMOOTH, LOW VOC, SOUND INSULATING, ELASTIC POLYURETHANE FLOOR COVERING WITH OPTIONAL COLOUR FLAKES

PRODUCT DESCRIPTION

Sika Comfortfloor® PS-66 is an elastic polyurethane self-smoothing flooring system and is part of the Sika Comfortfloor® decorative flooring range. Sika Comfortfloor® PS-66 optimizes a balance between comfort and aesthetics by combining softness under foot and individual design. Sika Comfortfloor® PS-66 is an ergonomic, sound dampening, low emission floor which is UV stable, highly aesthetical, easy to care for and to maintain and is especially designed for indoor applications where high comfort under feet, individual design, a jointless surface and soft footfall are required.

USES

Sika Comfortfloor® PS-66 installation works to be carried out only by Sika Approved Contractors. Please observe information given by Product Data Sheets.

- Commercial and public buildings
- Healthcare facilities
- Schools
- Retail spaces & laboratories
- Nursing facilities
- Showrooms & lobbies
- Museums and office space.

CHARACTERISTICS / ADVANTAGES

- Low VOC emission
- Highly decorative
- Flexible and resilient
- Very good acoustic isolation
- Good mechanical resistance
- Good UV resistance
- Reduces footfall sound

- Attractive colours available using pigmented UV stable base coat
- Non shrinking after cure
- High strength
- Low maintenance and life cycle cost
- Tough, durable and seamless floor

ENVIRONMENTAL INFORMATION

- Emissions tested at Eurofins according to the AgBB- and CDPH rule 01350 schemes and guidelines. Sampling, testing and evaluation were performed according to ISO-16000, Reports No. 770028A


APPROVALS / STANDARDS

- Reaction to Fire classification according to DIN EN 13501-1. Test institute Hoch Report No. KB-Hoch-141425 for the Sika Comfortfloor® Decorative Pro.
- Cleanroom® suitable material as part of the Sika ComfortFloor® Decorative Pro system sealed with Sikafloor®-304W. Tested on Biological resistance by Fraunhofer IPA, Germany report no. SI 1008- 533
- Impact sound reduction according EN ISO 140-8, test report 102-B-08, iba Institut Gottfried & Rolof Germany.
- Determination of wear resistance EN651:2004 , indentation EN 433:2004, and effect of simulated movement of furniture leg according EN 424:2002 reports 391582-02 TFI institute Aachen Germany.

SYSTEM INFORMATION

System Structure

Sika Comfortfloor® PS-66



Layer	Product
1. Adhesive	Sikafloor® Comfort Adhesive
2. Shockpad	Sikafloor® Comfort Regupol® 4580
3. Porefiller	Sikafloor® Comfort Porefiller
4. Base coat	Sikafloor®-3000
5. Top coat	Sikafloor®-304W

As optional base coats Sikafloor®-300 can be used. Note that the approvals on emissions will be affected. Please refer to the individual Product Data Sheet.

Composition	Polyurethane
Appearance	Smooth, matt finish
Colour	Available in almost unlimited choice of colour shades.
Nominal Thickness	~ 6 mm
Volatile organic compound (VOC) content	Very low content of Volatile Organic Compounds. It fulfils the stringent demands for indoor air quality and low VOC emitting products AgBB

TECHNICAL INFORMATION

Shore A Hardness	~84 (14 days /+23 °C)	(DIN 53505)
Resistance to Wearing	Wearing group M	(EN 660-2:1999)
Resistance to moving furniture	No damage	(EN 424:2002)
Castor chair resistance	No damage (25000 cycles)	(EN 425:1994)
Resistance to Impact	Class II	(ISO 6272)
Indentation	~ 0.1 mm	(EN 433:1994)
Tensile Adhesion Strength	> 1.5 N/mm ²	(EN 13892-8)
Reaction to Fire	Cfl-s1	(EN 13501-1)
Chemical Resistance	Sika Comfortfloor® PS-66 always has to be sealed with Sikafloor®-304 W. Refer to the chemical resistance of Sikafloor®-304 W.	
Capillary Absorption	< 0.01 kg/(m ² h ^{0.5})	(EN 1062-3)
Permeability to CO2	> 50 meter	(EN 1062-6)
Sound Insulation	17 dB	(EN ISO 140-8)

APPLICATION INFORMATION

Consumption	Layer	Product	Consumption
	1. Adhesive	Sikafloor® Comfort Adhesive	~0.9 kg/m ²
	2. Shockpad	Sikafloor® Comfort Regupol® 4580	~4 mm
	3. Porefiller	Sikafloor® Comfort Porefiller	~0.4 kg/m ² /layer
	4. Base coat	Sikafloor®-3000	~2.8kg/m ² (2 mm)
	5. Top coat	Sikafloor®-304W + 5% water	~0.15 kg/m ² /layer

Consumptions are theoretical and do not include any wastage or additional materials needed due to porosity, substrate profile etc.

Product Temperature	+15 °C min. / +30 °C max.
Ambient Air Temperature	+15 °C min. / +30 °C max.
Relative Air Humidity	80 % max.
Dew Point	Beware of condensation! The substrate and uncured floor must be at least 3°C above dew point to reduce the risk of condensation or other disturbance of the surface on the floor finish
Substrate Temperature	+15 °C min. / +30 °C max.
Substrate Moisture Content	Sika Comfortfloor® PS-66 can be installed on substrates with moisture content of max. 3 % (checked by Tramex). The substrate needs to be visibly dry and have adequate pull-off strength min 1.5 N/mm ² . Check rising moisture.

Applied Product Ready for Use	Temperature	Foot traffic	Light traffic	Full cure
	+15 °C	~ 30 hours	~ 48 hours	~ 6 days
+20 °C	~ 16 hours	~ 24 hours	~ 4 days	
+30 °C	~ 12 hours	~ 18 hours	~ 3 days	

Note: Times are approximate and will be affected by changing ambient and substrate conditions

PRODUCT INFORMATION

Packaging	Please refer to the individual Product Data Sheets
Shelf Life	Please refer to the individual Product Data Sheets
Storage Conditions	Please refer to the individual Product Data Sheets

MAINTENANCE

Please refer to the Sikafloor®- Cleaning Regime

CLEANING

FURTHER DOCUMENTS

Substrate Quality & Preparation

Please refer to Sika Information Manual: "Evaluation and preparation of surfaces for flooring systems".

Application Instructions

Please refer to Sika Information Manual: "Mixing & Application of flooring systems".

Maintenance

Please refer to "Sikafloor®- Cleaning regime".

LIMITATIONS

- Freshly applied Sikafloor® products must be protected from damp, condensation and water for at least 24 hours.
- Uncured material reacts in contact with water (foaming).
- During application care must be taken that no sweat drops into fresh Sikafloor® products (wear head and wrist bands).
- For exact colour matching, ensure the Sikafloor® product in each area is applied from the same control batch number.
- Under certain conditions, underfloor heating or high ambient temperatures combined with high point loading, may lead to imprints in the resin.
- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

Local safety regulations must be observed and it advisable to wear PPI when working with this product with particular attention paid to cutting and handling.

Transportation Class: The product is not classified as hazardous good for transport. Disposal: The material is recyclable. Disposal must be according to local regulations. Please contact your local Sika sales organisation for more information.

SIKA IRELAND LIMITED

Ballymun Industrial Estate

Ballymun

Dublin 11, Ireland

Tel: +353 1 862 0709

Web: www.sika.ie

Twitter: @Sikalreland



System Data Sheet

Sika Comfortfloor® PS-66

November 2019, Version 03.01

020812900000000004

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaComfortfloorPS-66-en-IE-(11-2019)-3-1.pdf