

SYSTEM DATA SHEET

Sikafloor® MultiDur EB-31

BROADCAST UNICOLOUR EPOXY FLOOR COVERING WITH HIGH CHEMICAL AND MECHANICAL RESISTANCE

PRODUCT DESCRIPTION

Sikafloor® MultiDur EB-31 is a slip resistant, coloured epoxy covering with high chemical and mechanical resistance for flooring applications

USES

Sikafloor® MultiDur EB-31 installation works to be carried out only by Sika Approved Contractors. Please observe information given by Product Data Sheets.

- Suitable for concrete and screed surfaces in areas with high chemical and mechanical exposures.
- Production and processing areas in food industry and automotive industry

CHARACTERISTICS / ADVANTAGES


- High chemical resistance
- High mechanical resistance
- Liquid proof
- Slip resistant

APPROVALS / STANDARDS

- Slip resistance certificate according to DIN 51130, class R12 V8, Report No.020108-13-19, Roxeler Institute, October 2013, Germany

SYSTEM INFORMATION

System Structure



Sikafloor® MultiDur EB-31 system (~ 2–3 mm)

1. Primer	Sikafloor®-156/-161
2. Wearing coat & broadcast	Sikafloor®-381 & broadcast with silicon carbide 0.5–1.0 mm or quartz sand 0.3–0.8 mm
3. Top coat	Sikafloor®-381 + 5 % by weight Thinner C

Composition	Epoxy
Appearance	Slip resistant, gloss finish
Colour	Available in various colour shades.
Nominal Thickness	~2.0–3.0 mm

TECHNICAL INFORMATION

Chemical Resistance	Refer to the chemical resistance of Sikafloor®-381	
Thermal Resistance	Exposure*	Dry heat
	Permanent	+50 °C
	Short-term max. 7 d	+80 °C
	Short-term max. 12 h	+100 °C
Short-term moist/wet heat* up to +80 °C where exposure is only occasional (i.e. during steam cleaning etc.)		
*No simultaneous chemical and mechanical exposure.		
Skid / Slip Resistance	R12 V 8	(DIN 51130)

APPLICATION INFORMATION

Consumption	Sikafloor® MultiDur EB-31 system (~ 2–3 mm)		
	Coating System	Product	Consumption
	Primer	Sikafloor®-156/-161	~ 0.3–0.5 kg/m ²
	Wearing coat	Sikafloor®-381 (unfilled)	~ 1.6 kg/m ²
	Broadcast in excess	Silicon Carbide 0.5–1.0 mm or quartz sand 0.3–0.8 mm	~ 4–6 kg/m ²
Top coat	Sikafloor®-381 + 5 % by weight Thinner C	~0.75–0.85 kg/m ²	

Product Temperature	Please refer to the individual Product Data Sheet
----------------------------	---

Ambient Air Temperature	+10 °C min. / +30 °C max.			
Relative Air Humidity	80 % r.h. max.			
Dew Point	Beware of condensation! The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or blooming on the floor finish.			
Substrate Temperature	+10 °C min. / +30 °C max.			
Substrate Moisture Content	When performing application work with Sikafloor® MultiDur EB-31, the substrate moisture content must not exceed 4 % pbw measured by Tramex. Test method: Sika®-Tramex meter, CM - measurement or Oven-dry-method. No rising moisture according to ASTM (Polyethylene-sheet).			
Waiting Time / Overcoating	Before applying Sikafloor®-381 on Sikafloor®-156/-161 allow:			
	Substrate temperature	Minimum	Maximum	
	+10 °C	24 hours	4 days	
	+20 °C	12 hours	2 days	
	+30 °C	8 hours	1 day	
	Before applying Sikafloor®-381 on Sikafloor®-381 allow:			
	Substrate temperature	Minimum	Maximum	
	+10 °C	24 hours	48 hours	
	+20 °C	18 hours	24 hours	
	+30 °C	6 hours	12 hours	
Applied Product Ready for Use	Temperature	Foot traffic	Light traffic	Full cure
	+10 °C	~ 24 hours	~ 3 days	~ 10 days
	+20 °C	~ 18 hours	~ 2 days	~ 7 days
	+30 °C	~ 12 hours	~ 1 day	~ 5 days

PRODUCT INFORMATION

Packaging	Please refer to the individual Product Data Sheets
Shelf Life	Please refer to the individual Product Data Sheets
Storage Conditions	Please refer to the individual Product Data Sheets

MAINTENANCE

CLEANING

Please refer to the Information Manual Sikafloor®-Cleaning Regime

FURTHER DOCUMENTS

- Sika® Information Manual Mixing & Applications of Flooring systems
- Sika® Information Manual Evaluation and Preparation of Surfaces for Flooring systems

LIMITATIONS

- Do not apply Sikafloor® MultiDur EB-31 on substrates with rising moisture.
- Freshly applied Sikafloor® MultiDur EB-31 must be protected from damp, condensation and water for at least 24 hours.
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.
- For exact colour matching, ensure the Sikafloor®-381 in each area is applied from the same control batch numbers.

- Under certain conditions, underfloor heating or high ambient temperatures combined with high point loading, may lead to imprints in the resin.
- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

Local safety regulations must be observed and it advisable to wear PPI when working with this product with particular attention paid to cutting and handling. Transportation Class: The product is not classified as hazardous good for transport. Disposal: The material is recyclable. Disposal must be according to local regulations. Please contact your local Sika sales organisation for more information.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @Sikalreland



System Data Sheet

Sikafloor® MultiDur EB-31
November 2019, Version 01.01
020811900000000041

SikafloorMultiDurEB-31-en-IE-(11-2019)-1-1.pdf

