

PRODUCT DATA SHEET

Sika® BituSeal Primer

BituSeal Primer

PRODUCT DESCRIPTION

Sika® BituSeal Primer is a bitumen solution to be used in conjunction with Sika® BituSeal S-115.

USES

Sika® BituSeal Primer is used as a primer for Sika® BituSeal S-115 to increase adhesion and bond to the substrate.

CHARACTERISTICS / ADVANTAGES

- High adhesion and bonding ability on various substrates
- Good binding ability for dust and loose particles
- Ready to use by brush, roller or spray

PRODUCT INFORMATION

Chemical Base	Bitumen Solution
Packaging	25 ltr drums
Shelf Life	18 months from date of production.
Storage Conditions	Store in dry conditions between +5°C to +35°C. They must be protected from direct sunlight, rain, snow and ice.
Colour	Black liquid
Flash Point	> 39°C
Viscosity	500 cP

APPLICATION INFORMATION

Consumption	Rate: approx. 350g/m ² depending on substrate type and temperature Coverage: 6-8m ² /ltr WFT: 90-110 microns DFT: 45-60 microns
-------------	----------------------------------------------------------------------------------------------------------------------------------------------------------------

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

Local safety regulations must be observed and it advisable to wear PPI when working with this product with particular attention paid to cutting and handling. Transportation Class: The product is not classified as hazardous good for transport. Disposal: The material is recyclable. Disposal must be according to local regulations. Please contact your local Sika sales organisation for more information.

APPLICATION INSTRUCTIONS

Application Method / Tools

Application by brush or roller.

Waiting time, depending to temperature, > 30min. unless drying.

For more detailed information, please refer to the current Method Statement of the according system.

Notes on Application / Limits

This product must not be installed on wet substrates.

Apply at temperatures above +10°C. At lower temperatures, use a hot air gun or indirect flame to aid adhesion.

Never attempt to apply at temperatures below +5°C.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @Sikalreland



Product Data Sheet

Sika® BituSeal Primer
June 2022, Version 01.01
020725601000000001

SikaBituSealPrimer-en-IE-(06-2022)-1-1.pdf

