

PRODUCT DATA SHEET

SikaPlast®-115

Mid-Range Water Reducing/Plasticising Concrete Admixture

PRODUCT DESCRIPTION

SikaPlast®-115 is a liquid admixture for concrete which is used as a mid-range water reducer/plasticiser. It meets the requirement of IS EN 934 -2.

USES

- SikaPlast®-115 is suitable for the production of ready mixed concrete
- Applications that require high quality concrete
- Applications that require improved consistence retention
- Utilisation of crushed rock fines in concrete

- Improved early and ultimate strengths
 - Improved rheology
 - Improved durability
 - Reduced segregation and bleeding
 - Reduced drying shrinkage
 - Reduced mix costs
- * Compared to concrete without admixture

APPROVALS / STANDARDS

Conforms to the requirements of IS EN 934-2 Table 3.1 DoP 13196953, certified by Factory Production Control Body 1029 and provided with the CE mark.

CHARACTERISTICS / ADVANTAGES

- Mid-range water reductions resulting in higher strengths and densities
- Flexible application as both WRA and HRWR
- Less sensitive to variations in cement and aggregate types
- Improved cohesion properties

PRODUCT INFORMATION

Chemical Base	Modified polycarboxylate blend
Packaging	20 litre drum, 1000 litre IBC
Appearance / Colour	Brown liquid
Shelf Life	12 months from date of production if stored properly in undamaged containers.
Storage Conditions	Store in dry conditions at temperatures between +5°C and +25°C. Protect from direct sunlight and frost.
Total Chloride Ion Content	<0.1 % (chloride free)
Equivalent Sodium Oxide	<0.50 % (alkali content)
Specific gravity	1.1 kg/L (at +20°C)

TECHNICAL INFORMATION

Specific Advice

Effect on Setting: Slight extension to normal setting
Effect of Overdosing: Increased workability and segregation
SikaPlast®-115 should not be added to dry cement
SikaPlast®-115 should be added with the mixing water
Support from our Technical Service Department is recommended

APPLICATION INFORMATION

Recommended Dosage

0.3 – 1.5 % by weight of cement. Exact dose should be confirmed by trial and may fall outside this range.

Compatibility

Sika Admixtures:
▪ Compatibility information available on request
Cements:
▪ All cement combination

Dispensing

SikaPlast®-115 should be dispensed through suitable calibrated dosing equipment.

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

Application Method / Tools

- The standard rules of good concreting practice, concerning production as well as placing, are to be followed. Refer to relevant standards. Fresh concrete must be cured properly.
- SikaPlast®-115 should not be added to dry cement
- SikaPlast®-115 should be added with the mixing water

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @SikaIreland



Product Data Sheet

SikaPlast®-115
April 2025, Version 01.01
021301011000004287

SikaPlast-115-en-IE-(04-2025)-1-1.pdf

