

PRODUCT DATA SHEET

Sikagard[®]-62

2-PART EPOXY PROTECTIVE COATING

PRODUCT DESCRIPTION

Sikagard[®]-62 is a two part, rigid, 100 % solids, coloured high build epoxy resin based protective coating.

USES

Sikagard[®]-62 installation works to be carried out only by Sika Approved Contractors. Please observe information given by Product Data Sheets.

- Chemical resistant protective layer on concrete, stone, cementitious mortars and renderings, epoxy cement, epoxy resin based products and steel
- Lining in storage tanks and silos
- Anti-corrosion coating on steel in food processing plants, sewage works, farms, agricultural enterprises, chemical and pharmaceutical facilities and beverage industry

CHARACTERISTICS / ADVANTAGES

- Solvent free
- Good mechanical and chemical resistance
- High build
- Impervious to liquids
- Easy to mix and to apply

PRODUCT INFORMATION

Chemical Base	Epoxy resin	
Packaging	Part A	3.75 kg drums
	Part B	1.25 kg drums
Appearance / Colour	Light Grey, Light Green	
Shelf Life	Part A: 12 months	
	Part B: 12 months	
	From date of production if stored properly.	

ENVIRONMENTAL INFORMATION

Conformity with LEED v2009 IEQc 4.2: Low-Emitting Materials - Paints and Coatings

APPROVALS / STANDARDS

- Coating for concrete protection according the requirements of EN 1504-2:2004, Declaration of Performance 0206060100100000011008, certified by FPC Notified Body and provided with CE marking
- DWI, Reference No. DWI.56.4.197, Approved under Regulation 31(4)(A) of the Water Supply (water Quality) Regulations 2016 SI No.614

Storage Conditions

The packaging must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5 °C and +30 °C. Protected from direct sunlight.

Density	Part A	~1.45 kg/l	(EN ISO 2811-1)
	Part B	~1.02 kg/l	
Mixed resin approx. ~1.37 kg/l Density values determined at +23°C			
Solid Content	~ 100 %		

TECHNICAL INFORMATION

Shore D Hardness	~80		(DIN 5305)
Mechanical Resistance	Taber Abraser	CS 10/ 1000/ 1000	24.4mg (ASTM D 4060)
	Taber Abraser	CS 17/ 1000/ 1000	70 mg
	Taber Abraser	H 22/ 1000/ 1000	560.6mg
Tensile Adhesion Strength	> 1.5 N/mm ² to concrete		(ISO 4624)
Chemical Resistance	Please contact Sika technical service for specific information.		
Thermal Resistance	Exposure	Dry heat	
	Permanent	+50 °C	
	max. 7 days	+80 °C	
	max. 12 hours	+100 °C	

APPLICATION INFORMATION

Mixing Ratio	Part A : Part B = 3 : 1 by weight			
Consumption	~0.30 kg/m ² per layer			
Layer Thickness	~0.2 mm per layer			
Ambient Air Temperature	+8 °C min. / +40 °C max.			
Relative Air Humidity	< 80 %			
Substrate Temperature	+8 °C min. / +40 °C max. Minimum 3 °C above dew point, beware of condensation			
Pot Life	Temperature	Time		
	+10 °C	~30 min		
	+20 °C	~20 min		
	+30 °C	~10 min		
Waiting Time / Overcoating	Temperature	Min.	Max.	Full cure
	+10 °C	~ 30 hours	~ 3 days	~ 14 days
	+20 °C	~ 10 hours	~ 2 days	~ 10days
	+30 °C	~ 6 hours	~ 1 day	~ 5 days

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The substrate must be sound, clean, dry, free from contaminants such as dirt, grease, oil, old coatings, release agents, laitance and other adhesion preventing or influencing substances.

On high absorbent, non-sound, contaminated, not ce-

ment based substrates precautions have to be taken and a suitable primer has to be used.

SUBSTRATE PREPARATION

Concrete Substrate

Concrete substrate must be prepared mechanically to achieve an open textured surface.

Weak areas in the substrate must be removed and surface defects such as blowholes and voids must be fully

exposed.

All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum. Open voids and blowholes need to be closed with a suitable Sika® pore filling mortar. The roughness of the substrate needs to be levelled with a suitable Sika® rendering and levelling mortar.

Steel Surface

Steel surface must be prepared mechanically using abrasive blast cleaning. The level SSPC-SP 10 "near white metal blast cleaned" or level Sa 2 ½ according to ISO EN 12944-4 has to be achieved. Welds and joints have to be prepared according to EN 14879, part 1. After blast cleaning remove all dust dirt and blasting material. In order to maintain the surface conditions after blast cleaning air-conditioning is recommended.

MIXING

Prior to mixing stir part A mechanically. When all of part B has been added to part A mix continuously for 3 minutes until a uniform mix has been achieved. Use a low speed electrical stirrer (300–400 rpm) to avoid air entrapment. To ensure proper mixing pour material into a clean container and stir again.

APPLICATION

Apply by brush, roller or airless spray.

CLEANING OF TOOLS

Clean all tools with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

LIMITATIONS

- Do not apply Sikagard®-62 on moist substrates
- Sag resistance on vertical surface is approx. 200 µm.
- Freshly applied Sikagard®-62 must be protected from damp, condensation and water for at least 24 hours
- For exact colour matching ensure using material from the same control batch numbers.

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

Local safety regulations must be observed and it advisable to wear PPI when working with this product with particular attention paid to cutting and handling. Transportation Class: The product is not classified as hazardous good for transport. Disposal: The material is recyclable. Disposal must be according to local regulations. Please contact your local Sika sales organisation for more information.

DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

According to the EU-Directive 2004/42, the maximum allowed content of VOC (Product category IIA / j type sb) is 550 / 500 g/l (Limits 2007 / 2010) for the ready to use product. The maximum content of Sikagard®-62 is < 500 g/l VOC for the ready to use product.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @Sikalreland



Product Data Sheet
Sikagard®-62
June 2019, Version 04.01
020606010010000001

Sikagard-62-en-IE-(06-2019)-4-1.pdf

