

## PRODUCT DATA SHEET

# SikaCeram® CleanGrout

Cementitious floor and wall tile grout for joints 1–8 mm

### PRODUCT DESCRIPTION

SikaCeram® CleanGrout is a cementitious powder floor and wall tile grout for use in joints from 1–8 mm in width. Additives contained in the powder provide protection against mould, bacterial and fungal growth while maintaining a colour stable, abrasion resistant, water repellent durable finish.

### USES

Grouting the following tile types:

- Ceramic
- Earthenware
- Glass mosaic
- Marble and other natural stones
- Grès porcelain

Grouting tiles for the following high performance and demanding applications:

- Swimming pools (excluding sea water and other aggressive treatments)
- Heated floors
- Commercial / Industrial / Residential environments
- Facades
- Interior and exterior use

### CHARACTERISTICS / ADVANTAGES

- Floor and wall application
- Water-repellent
- Abrasion resistant
- High degree of hardness
- UV resistant
- Frost proof
- Contains mould protection

### APPROVALS / STANDARDS

EN 13888: CG2WA

### PRODUCT INFORMATION

<b>Product Declaration</b>	EN 13888: CG2WA
<b>Chemical Base</b>	Polymer modified, portland cement based, with selected fine silica/quartz sand, water retainers and other special additives.
<b>Packaging</b>	5 kg bags. Refer to current price list for packaging variations.
<b>Shelf Life</b>	24 months from date of production.
<b>Storage Conditions</b>	The product must be stored in original, unopened and undamaged packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.
<b>Appearance / Colour</b>	Colours:

White	Light Grey	Silver	Manhattan	Ice
Grey	Ash	Anthracite	Graphite	Total black
Pergamon	Jasmine	Anemone	Beige	Pine
Caramel	Maple wood	Dove Grey	Light Sand	Sand
Cedar	Beech wood	Walnut	Oak wood	Brown
Terracotta	Amaranth	Ruby	Dark Brown	Mahogany

<b>Maximum Grain Size</b>	D <sub>max</sub> : 0.25 mm		
<b>Water Absorption</b>	After 30 minutes	≤ 1 g	(EN 12808-5)
	After 240 minutes	≤ 3 g	

## TECHNICAL INFORMATION

<b>Abrasion Resistance</b>	≤ 1000 mm <sup>3</sup>		(EN 12808-2)
<b>Compressive Strength</b>	After dry storage	≥ 20 N/mm <sup>2</sup>	(EN 12808-3)
	After freeze/thaw cycles	≥ 15 N/mm <sup>2</sup>	
<b>Flexural Strength</b>	After dry storage	≥ 4 N/mm <sup>2</sup>	(EN 12808-3)
	After freeze/thaw cycles	≥ 3 N/mm <sup>2</sup>	
<b>Shrinkage</b>	≤ 3 mm/m		(EN 12808-4)
<b>Microbiological Resistance</b>	Bacteria survival	0 %	(Protocol CCB - RP 335/10/S)
	Colonization	No growth	
<b>Joint width</b>	1–8 mm		

## APPLICATION INFORMATION

<b>Mixing Ratio</b>	5 kg bag	~1.3 litres of water	(26 % ± 1 %)
<b>Fresh mortar density</b>	~2.05 kg/l		

**Consumption** The consumption is dependent on the size of the tiles, joint width and depth.

**Consumption guide: g/m<sup>2</sup>**

Tile Size Centimetres	Joint Width			
	2 mm	3 mm	5 mm	8 mm
Glass mosaic	1300	-	-	-
2 × 2 × 0.4				
5 × 5 × 0.4	450			
10 × 10 × 0.6	350	500	840	1350
15 × 15 × 0.9	350	500	840	1350
20 × 20 × 0.9	250	380	630	1000
30 × 30 × 1	190	280	470	750
30 × 60 × 1	140	210	350	560
50 × 50 × 1	110	170	280	450
60 × 120 × 1.1	80	110	200	310

These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level, wastage or any other variations. Apply product to a test area to calculate the exact consumption for the specific substrate conditions and proposed application equipment.

Consumption can be also calculated with the following formula:

$$\text{Consumption (g/m}^2\text{)} = A \times B \times [(C + D)/(C \times D)] \times 140.$$

A = Gap width (mm)

C = Tile length (cm)

B = Tile height (mm)

D = Tile width (cm)

<b>Ambient Air Temperature</b>	+5 °C min. / +35 °C max.		
<b>Substrate Temperature</b>	+5 °C min. / +35 °C max.		
<b>Pot Life</b>	~2 hours		
<b>Waiting time</b>	<b>Before grouting on floor tiles laid with</b>	<b>Waiting time</b>	
	Normal-setting adhesive	24–36 hours	
	Fast-setting adhesive	4–6 hours	
	Thick-bed (traditional) adhesive	8–10 days	
	<b>Before grouting on wall tiles laid with</b>	<b>Waiting time</b>	
	Normal-setting adhesive	4–6 hours	
	Fast-setting adhesive	2 hours	
	Above times are indicative. Always consult the appropriate tile adhesive Product Data Sheet.		
	<b>Applied Product Ready for Use</b>	<b>Use</b>	<b>Waiting time</b>
		Pedestrian traffic	24–36 hours
	Full traffic	~14 days	
	Water immersion	~21 days	

## VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LIMITATIONS

- Do not exceed the recommended amount of water in the mix. The mix must never be fluid.
- The product is not suitable for chemical exposure. Use an epoxy grout from the range of SikaCeram® products.
- Prevent contact of freshly applied material with water (including rain), except during cleaning operations. Also prevent exposure with excess atmospheric humidity / condensation or residual moisture in the substrate etc.
- Avoid significant temperature variations during application and setting times, as well as excessive draughts, forced ventilation or winds.
- Excess water and ventilation, temperature variations, application on very porous tiles or on substrates leading to rapid water absorption etc. can result in colour shade variations.
- When coloured grout is applied for aesthetics such as on polished porcelain or natural stone tiles, always carry out cleanability testing on a small area prior to full application.
- On highly absorbent tiles, it is always recommended to thoroughly pre-dampen the surface before grouting.
- Always apply SikaCeram® CleanGrout in a continuous operation and do not interrupt for more than two hours in the same room or area of tiling.
- Premature exposure to water or excess water in the mix can result in white efflorescence on the grout surface.
- Avoid application in direct sunlight to avoid cracking in the joint.

- To avoid grout removal from joint, ensure grout has set sufficiently before carrying out the tile cleaning procedure.
- Do not add anything to the product that is not specified in this Product Data Sheet.
- Do not use for any applications not explicitly described in this Product Data Sheet.

## ECOLOGY, HEALTH AND SAFETY

Local safety regulations must be observed and it advisable to wear PPI when working with this product with particular attention paid to cutting and handling. Transportation Class: The product is not classified as hazardous good for transport. Disposal: The material is recyclable. Disposal must be according to local regulations. Please contact your local Sika sales organisation for more information.

# APPLICATION INSTRUCTIONS

## EQUIPMENT

Select the most appropriate equipment required for the project:

### Mixing equipment

- Low speed electric single or double paddle mixer (500 rpm) with spiral paddle.

### Application equipment

- Grout spreader
- Squeegee
- Grouting float/trowel
- Sponge
- Soft cloth
- Grout finishing tool

## SUBSTRATE QUALITY / PRE-TREATMENT

- Check joints are dry, clean, and clear of excess adhesive, contaminants and tile joint spacers. Remove from joint before grout application.
- For applications in hot climates / environments, or on absorbent substrates, thoroughly pre-dampen the surface immediately prior to product application.
- Avoid any ponding / standing water on the surface.
- Surface must not be damp to touch.

## MIXING

### IMPORTANT

Avoid over-mixing to minimise air entrainment.

### IMPORTANT

Do not add additional water into the mixed product during or after mixing.

### IMPORTANT

Do not exceed the recommended amount of water in the mix. The mix must never be fluid.

Note: For high-performance and demanding applications, such as heavily trafficked floors, exposed facades, swimming pools or for additional flexibility: replace water with a solution of SikaCeram® LatexGrout (Refer to the individual Product Data Sheet).

Requirement: Use a low speed electric single paddle mixer (500 rpm) with a spiral mixing paddle.

1. Pour the recommended amount of clean cold water into a clean mixing container.
2. Gradually add SikaCeram® CleanGrout powder to the water while mixing.
3. Mix thoroughly until a uniformly coloured, smooth mix is achieved.
4. Do not mix for 2–3 minutes to allow mixed product to 'mature'.
5. Remix for ~30 seconds.

### SIKA IRELAND LIMITED

Ballymun Industrial Estate  
Ballymun  
Dublin 11, Ireland  
Tel: +353 1 862 0709  
Web: [www.sika.ie](http://www.sika.ie)  
Twitter: @Sikalreland



### Product Data Sheet

SikaCeram® CleanGrout  
April 2022, Version 04.01  
02172010000000017

## APPLICATION

### IMPORTANT

Check adhesive has fully set before grouting.

Note: When using SikaCeram® LatexGrout instead of water in the grout mix, immediately polish the tiles after the initial cleaning with a damp sponge.

1. Apply SikaCeram® CleanGrout using a grout spreader, squeegee or grouting float/trowel.
2. Completely fill and compact the joints uniformly.
3. If required, finish grout with a grout finishing tool while grout is wet.
4. Using the same spreader/ float, remove excess grout from the tile surfaces moving the tool diagonally across the joints.
5. When the grout is touch dry, use a damp sponge or sponge float to clean the tile surfaces. Clean sponge regularly with clean water.
6. When the grout has set hard enough in the joint (finger-nail hard), polish the tile surfaces by wiping with a clean, soft dry cloth.

## CLEANING OF TOOLS

Clean all tools and application equipment with water after use. Hardened material can only be removed mechanically.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaCeramCleanGrout-en-IE-(04-2022)-4-1.pdf

