

## PRODUCT DATA SHEET

# Sika® Permacor®-2330

### 2-PACK AY-PUR TOP COAT

#### PRODUCT DESCRIPTION

Sika® Permacor®-2330 is a 2-pack acrylic polyurethane top coat.

#### USES

Sika® Permacor®-2330 installation works to be carried out only by Sika Approved Contractors. Please observe information given by Product Data Sheets.

Sika® Permacor®-2330 is used as mechanical resistant topcoat for atmospherically exposed steel surfaces - also for condensation - particularly for machinery, paper mills, engines, rollercoasters and commercial vehicles.

In combination with 2-pack primers and intermediate coats of the SikaCor® and Sika® Permacor® range Sika® Permacor®-2330 offers a mechanical resistant coating system for long-life corrosion protection with high weather resistance up to corrosivity category C5 high, acc. ISO 12944-5.

#### CHARACTERISTICS / ADVANTAGES

- Very high weather resistance and gloss- and colour retention
- Applicable also at low temperatures down to 0°C

#### APPROVALS / STANDARDS

- Approved according to German standard 'TL/TP-KOR-Stahlbauten', page 87 and page 97.
- Tested according to NORSOK Standard M-501, rev. 6, system no. 1.

#### PRODUCT INFORMATION

<b>Packaging</b>	Sika® Permacor®-2330	28.75 kg and 11.5 kg net.
	Sika® Thinner P	25 l and 5 l
<b>Appearance / Colour</b>	RAL- and NCS-colour shades, glossy Others upon request.	
<b>Shelf Life</b>	2 years	
<b>Storage Conditions</b>	In originally sealed containers in a cool and dry environment.	
<b>Density</b>	~1.3 kg/l	
<b>Solid Content</b>	~56 % by volume	
	~69 % by weight	

## TECHNICAL INFORMATION

<b>Chemical Resistance</b>	Weathering, water, sewage, seawater, smoke, de-icing salts, acid and lye vapours, oils, grease and short term exposure to fuels and solvents.
<b>Thermal Resistance</b>	Dry heat up to approx. + 120°C, short term up to + 150°C Damp heat up to approx. + 50°C

## SYSTEM INFORMATION

<b>Systems</b>	<p>Suitable as topcoat on primers and intermediate coats of Sika® Permacor® Systems 2000, 2200 and 2300.</p> <p><u>Steel:</u> 1 x Sika® Permacor®-2204 VHS 1 x Sika® Permacor®-2330 or 1 x Sika® Permacor®-2311 Rapid 1 x Sika® Permacor®-2215 VHS 1 x Sika® Permacor®-2330</p> <p>Also possible as alternative top coat in SikaCor® EG-System and SikaCor® EG-System Rapid.</p> <p><u>Hot dip galvanized steel, stainless steel and aluminium:</u> 1x SikaCor® EG-1 1x Sika® Permacor®-2330</p>
----------------	--

## APPLICATION INFORMATION

<b>Mixing Ratio</b>	Components A : B	
	By weight	100 : 15
	By volume	5.1 : 1
<b>Thinner</b>	Sika® Thinner P If necessary max. 5 % Sika® Thinner P may be added to adapt the viscosity.	
<b>Consumption</b>	Theoretical material-consumption/VOC without loss for medium dry film thickness:	
	Dry film thickness	50 µm                      80 µm
	Wet film thickness	90 µm                        145 µm
	Consumption	~0,115 kg/m <sup>2</sup> ~0,185 kg/m <sup>2</sup>
	VOC	~36,0 g/m <sup>2</sup> ~57.6 g/m <sup>2</sup>
<b>Product Temperature</b>	Min. + 5°C	
<b>Relative Air Humidity</b>	Max. 85 %, except the surface temperature is significantly higher than the dew point temperature, it shall be at least 3 K above dew point. The surface must be dry and free from ice.	
<b>Surface Temperature</b>	Min. 0°C	
<b>Pot Life</b>	At + 10°C	~8 h
	At + 20°C	~6 h
	At + 30°C	~3 h
<b>Drying Stage 6</b>	Drying stage 6 and waiting time between coats:	

	Dry film thickness 80 µm
0°C after	48 h
+ 5°C after	24 h
+ 10°C after	18 h
+ 15°C after	10 h
+ 20°C after	8 h
+ 25°C after	6 h
+ 30°C after	4 h

**Drying time**

Final drying time

The full hardness is achieved within approx. 7 days at + 20°C. Tests of the completed coating system should only be carried out after final curing.

**APPLICATION INSTRUCTIONS****SURFACE PREPARATION**Steel:

Blast cleaning to Sa 2 ½ according to ISO 12944-4. Free from dirt, oil and grease.

Hot dip galvanized steel, stainless steel and aluminium:

Free from dirt, oil, grease and corrosion products. In case of exposure to permanent condensation the surfaces must be slightly sweep blasted with a ferrite-free blasting abrasive.

For contaminated surfaces e.g. galvanized or primed areas we recommend to clean with SikaCor® Wash.

**MIXING**

Stir component A very thoroughly using an electric mixer (start slowly, then increase up to approx. 300 rpm). Add component B carefully and mix both components very thoroughly (including sides and bottom of the container). Mix for at least 3 minutes until a homogeneous mixture is achieved. Fill mixed material into clean container and mix again shortly as described above. During mixing and handling of the materials always wear protective goggles, suitable gloves and other protective clothings.

**APPLICATION**

The method of application has a major effect on achieving uniform thickness and appearance. Spray application will give the best results. The indicated dry film thickness is easily achieved by airless spray. Adding solvents reduces the sag resistance and the dry film thickness. In case of application by roller or brush, additional applications may become necessary to achieve the required coating thickness, depending on type of construction, site conditions, colour shade etc. Prior to major coating operations a test application on site may be useful to ensure the selected application method will provide the requested results.

By brush or rollerAirless-Spraying:

- Pressure min. 150 bar
- Nozzle size 0.38 - 0.53 mm (0.015 - 0.021 inch)

- Spraying angle 40° - 80°

**CLEANING OF TOOLS**

Sika® Thinner P

**VALUE BASE**

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

**LOCAL RESTRICTIONS**

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

**ECOLOGY, HEALTH AND SAFETY**

Local safety regulations must be observed and it advisable to wear PPI when working with this product with particular attention paid to cutting and handling. Transportation Class: The product is not classified as hazardous good for transport. Disposal: The material is recyclable. Disposal must be according to local regulations. Please contact your local Sika sales organisation for more information.

GISCODE: PU 50

This coding enables additional information and help with the creation of operating instructions (WINGIS online) to be obtained on the BG Bau service pages ([www.gisbau.de](http://www.gisbau.de)).

**DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC**

According to the EU Directive 2004/42/CE, the maximum allowed content of VOC (product category IIA / j type Sb) is 500 g/l (Limits 2010) for the ready to use product.

The maximum content of Sika® Permacor®-2330 is < 500 g/l VOC for the ready to use product.

**LEGAL NOTES**

The information, and, in particular, the recommenda-

tions relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**SIKA IRELAND LIMITED**

Ballymun Industrial Estate  
Ballymun  
Dublin 11, Ireland  
Tel: +353 1 862 0709  
Web: [www.sika.ie](http://www.sika.ie)  
Twitter: @Sikalreland



**Product Data Sheet**

Sika® Permacor®-2330  
November 2019, Version 03.01  
020602000210000007

SikaPermacor-2330-en-IE-(11-2019)-3-1.pdf

