

PRODUCT DATA SHEET

SikaCor® EG-1 Rapid

FAST CURING, HIGH-SOLID EPOXY-BASED INTERMEDIATE COAT

PRODUCT DESCRIPTION

SikaCor® EG-1 Rapid is a fast curing, 2-pack intermediate coat based on epoxy resin containing micaceous iron oxide.

Low solvent content according to Protective Coatings Directive of German Paint Industry Association (VdL-RL 04).

USES

SikaCor® EG-1 Rapid installation works to be carried out only by Sika Approved Contractors. Please observe information given by Product Data Sheets. Designed as a mechanically resistant intermediate coat on steel surfaces exposed to atmospheric conditions, hot dip galvanized steel, zinc spraying, stainless steel and aluminium.

In combination with 2-pack primer and top coats, SikaCor® EG-1 Rapid is a mechanically water and chemically resistant coating system for durable corrosion protection, corrosivity category C5 high, protection duration 'high' according to ISO 12944-2.

CHARACTERISTICS / ADVANTAGES

- Application at low temperatures till - 10°C
- Excellent adhesion to hot-dip galvanized steel, zinc spraying, stainless steel and aluminium
- High film thickness up to 120 µm per layer
- Very good corrosion protection properties
- Tough elastic and hard but not brittle
- Largely insensitive against shock and impact

APPROVALS / STANDARDS

- Approved according to German standard 'TL/TP-KOR-Stahlbauten, Blatt 97'.

PRODUCT INFORMATION

Packaging	SikaCor® EG-1 Rapid	28,5 kg net.
	Sika® Thinner EG	25 l, 10 l and 3 l
	SikaCor® Cleaner	160 l and 25 l
Appearance / Colour	Grey metallic approx. DB 701	
	Grey metallic approx. DB 702, mat.-no. 697.12	
	Grey metallic approx. DB 703, mat.-no. 697.13	
	Green metallic approx. DB 601, mat.-no. 697.14	
	White	
Slight colour deviations are possible due to raw material characteristics.		
Shelf Life	3 years	
Storage Conditions	In originally sealed containers in a cool and dry environment.	

Density	~1.6 kg/l
Solid Content	~56 % by volume ~77 % by weight

TECHNICAL INFORMATION

Chemical Resistance	Weather, water, sewage, seawater, smoke, de-icing salts, acid and lye vapours, oils, grease and short term exposure to fuels and solvents.
Thermal Resistance	Dry heat up to + 150°C, short term up to + 180°C Damp heat up to approx. + 50°C In case of higher temperatures please consult Sika.

SYSTEM INFORMATION

Systems	<p><u>Steel:</u> Used as intermediate coat on 2-pack primer coats of Sika for e.g.:</p> <ul style="list-style-type: none"> ▪ SikaCor® Zinc R ▪ SikaCor® Zinc R Rapid ▪ SikaCor® EG Phosphat ▪ SikaCor® EG Phosphat Rapid ▪ As intermediate coat on 1-pack primer coat SikaCor® Zinc ZS <p>Suitable top coats: Versatile overcoatable with 1 or 2-pack products of Sika</p> <p><u>Hot dip galvanized steel, thermal zinc spraying, aluminium and stainless steel:</u> 1 x SikaCor® EG-1 Rapid 1 x top coat (see above)</p>
---------	----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

APPLICATION INFORMATION

Mixing Ratio	Components A : B	
	By weight	94.7 : 5.3
	By volume	9.3 : 1
Thinner	Sika® Thinner EG If necessary max. 5% Sika Thinner® EG may be added to adapt the viscosity.	
Consumption	Theoretical material-consumption/VOC without loss for medium dry film thickness:	
	Dry film thickness	80 µm
	Wet film thickness	145 µm
	Consumption	~0.230 kg/m ²
	VOC	~52.6 g/m ²
	With SikaCor® EG-1 Rapid up to 120 µm dry film thickness per application can be achieved by spray.	
Product Temperature	Min. + 0°C	
Relative Air Humidity	Max. 85 %, except the surface temperature is significantly higher than the dew point temperature, it shall be at least 3 K above dew point. The surface must be dry and free from ice.	
Surface Temperature	Min. - 10°C	
Pot Life	At + 10°C	~8 h
	At + 20°C	~5 h
	At + 30°C	~2 h

Drying Stage 6

	Dry film thickness 80 µm
+ 0°C after	12 h
+ 5°C after	6 h
+ 10°C after	5 h
+ 20°C after	3 h

(ISO 9117-5)

Waiting Time / Overcoating

Min. until drying stage 6 is achieved
Max. 1 year
In case of longer waiting times please contact Sika.
SikaCor® EG-1 Rapid cures also at low temperatures below 0 °C. The revision intervals delayed significantly and have to be determined on site.

Prior to further applications possible contamination must be removed.

Drying time

Final drying time

Depending on film thickness and temperature full hardness is achieved after 1 - 2 weeks. Tests of the completed coating system should only be carried out after final curing.

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

Steel:

Blast cleaning to Sa 2 ½ according to ISO 12944-4.
Free from dirt, oil and grease.

Hot dip galvanized steel, stainless steel and aluminium:

Free from dirt, oil, grease and corrosion products.
In case of permanent immersion and condensation the surfaces must be slightly sweep blasted with a ferrite-free blasting abrasive.
Zinc spraying must be sealed and porefree.

For contaminated surfaces e.g. galvanized or primed areas we recommend cleaning with SikaCor® Wash.

MIXING

Stir component A very thoroughly using an electric mixer (start slowly, then increase up to approx. 300 rpm). Add component B carefully and mix both components very thoroughly (including sides and bottom of the container). Mix for at least 3 minutes until a homogeneous mixture is achieved. Fill mixed material into clean container and mix again shortly as described above. During mixing and handling of the materials always wear protective goggles, suitable gloves and other protective clothings.

APPLICATION

The method of application has a major effect on achieving uniform thickness and appearance. Spray application will give the best results. The indicated dry film thickness is easily achieved by airless spray. Adding solvents reduces the sag resistance and the dry film thickness. In case of application by roller or brush, additional applications may become necessary to achieve the required coating thickness, depending on type of construction, site conditions, colour shade etc.
Colour Stability: It is the natural tendency of epoxy products to discolorate (yellowing) whether used on internal or external areas. Therefore, any areas

touched-up and repaired with the same colour at a later date may be obvious due to this colour change. Prior to major coating operations a test application on site may be useful to ensure the selected application method will provide the requested results.

By brush and roller

Conventional high pressure spraying:

- Nozzle size 1.5 - 2.5 mm
- Pressure 3 - 5 bar
- Oil and water trap is compulsory

Airless-spraying:

- Pressure min. 180 bar
- Nozzle size 0.38 - 0.53 mm (0.015 - 0.021 inch)
- Spraying angle 40° - 80°

CLEANING OF TOOLS

SikaCor® Cleaner

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

Local safety regulations must be observed and it advisable to wear PPI when working with this product with particular attention paid to cutting and handling. Transportation Class: The product is not classified as hazardous good for transport. Disposal: The material is recyclable. Disposal must be according to local regulations. Please contact your local Sika sales organisation for more information.

DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

According to the EU Directive 2004/42/CE, the maximum allowed content of VOC (product category IIA / j type Sb) is 500 g/l (Limits 2010) for the ready to use product.

The maximum content of SikaCor® EG-1 Rapid is < 500 g/l VOC for the ready to use product.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA IRELAND LIMITED
Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @Sikalreland



Product Data Sheet
SikaCor® EG-1 Rapid
September 2019, Version 04.02
020602000040000008

SikaCorEG-1Rapid-en-IE-(09-2019)-4-2.pdf

