

PRODUCT DATA SHEET

Sika® Aer-46

AIR ENTRAINING CONCRETE ADMIXTURE

PRODUCT DESCRIPTION

Sika® Aer-46 is a liquid air entraining concrete admixture which is formulated from modified naturally occurring and synthetic surfactants. It meets the requirements of BS EN 934-2.

USES

- Sika® Aer-46 promotes the distribution of microscopic air bubbles throughout the cement matrix.
- Applications that require high resistance to freeze/thawing cycles
- Concrete that will be exposed to tidal conditions, splash zones and de icing salts

CHARACTERISTICS / ADVANTAGES

- Provides consistent bubble size and spacing
- Improved cohesion
- Improved workability
- Improved rheology
- Reduced permeability
- Reduced bleeding
- Reduced laitance, enhancing the concrete's resistance to frost attack
- Reduced loss of air from fresh concrete

APPROVALS / STANDARDS

Conforms to the requirements of BS EN 934-2 Table 5 DoP 02 14 03 02 100 0 000085 1088, certified by Factory Production Control Body 0086, Certificate 541325, and provided with the CE mark

PRODUCT INFORMATION

Chemical Base	Modified surfactants
Packaging	20 litre drum, 200 litre drum, 1000 litre IBC
Appearance / Colour	Clear Liquid
Shelf Life	12 months from date of production if stored properly in undamaged containers.
Storage Conditions	Store in dry conditions at temperatures between +5°C and +25°C. Protect from direct sunlight and frost.
Density	1.00 kg/l (at +20°C)
pH-Value	6.0 ± 1.0
Total Chloride Ion Content	<0.10% w/w (chloride free)
Specific Advice	Freezing Point : +1°C Effect of Overdosing : Increased air content leading to reduced densities and strength Alkali Content : <0.10% w/w
Effect on Setting	Negligible

APPLICATION INFORMATION

Recommended Dosage	0.1 -0.8% by weight of cement
Compatibility	Sika® Admixtures: <ul style="list-style-type: none">▪ Compatibility information available on request Cements: <ul style="list-style-type: none">▪ All cement combinations▪ Pulverised Fuel Ash (PFA) is a waste product of modern electricity generation. Only use PFA complying with the relevant British Standard in structural concrete. Such material will vary within the parameters laid down in the standard. Eg fineness, carbon content and loss on ignition. As a result, the amount of Sika® Aer-46 required may vary to maintain a specific air content.
Dispensing	Sika® Aer-46 should be dispensed through suitable calibrated dosing equipment.

APPLICATION INSTRUCTIONS

APPLICATION METHOD / TOOLS

- The standard rules of good concreting practice, concerning production as well as placing, are to be followed. Refer to relevant standards. Fresh concrete must be cured properly.
- Sika® Aer-46 should not be added to dry cement
- Sika® Aer-46 should be added with the mixing water

NOTES ON APPLICATION / LIMITATIONS

- When using Sika® Aer-46 a suitable mix design is required and local material sources should be evaluated.
- Due to the significant number of constituent, mix design, manufacture and placing related factors outside Sika's control, bubble spacing determination should be carried out by the concrete producer to ensure compliance with BS – EN 934-2. Bubble spacing should be completed using the specific concrete constituents/admixture combinations. For further information see CAA Admixture information sheet AIS 16 which is available at www.admixtures.org.uk
- Support from our Technical Department is recommended

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

Local safety regulations must be observed and it advisable to wear PPI when working with this product with

particular attention paid to cutting and handling.

Transportation Class: The product is not classified as hazardous good for transport. Disposal: The material is recyclable. Disposal must be according to local regulations. Please contact your local Sika sales organisation for more information.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA IRELAND LIMITED
Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @Sikalreland



Product Data Sheet
Sika® Aer-46
May 2019, Version 02.01
021403021000000085

SikaAer-46-en-IE-(05-2019)-2-1.pdf

