

SYSTEM DATA SHEET

Sikafloor® PurCem® HS-26 Gloss

GLOSS AND SMOOTH FINISH, POLYURETHANE CEMENT HYBRID FLOORING SYSTEM

PRODUCT DESCRIPTION

Sikafloor® PurCem® HS-26 Gloss is an industrial flooring system based on polyurethane cement hybrid technology and is part of the Sikafloor® PurCem® Gloss system range.

Sikafloor® PurCem® HS-26 Gloss consists of a primer or scratch coat layer and an extremely durable, gloss, scratch resistant and seamless polyurethane hybrid wearing course.

Sikafloor® PurCem® HS-26 Gloss withstands chemical attack, abrasion and impacts. Due its gloss, scratch resistant and impervious surface the flooring is easy to clean, maintain and hygienic.

USES

Sikafloor® PurCem® HS-26 Gloss installation works to be carried out only by Sika Approved Contractors. Please observe information given by Product Data Sheets.

- Food and beverage industry
- Workshops
- Storage rooms
- Hangars
- Parking decks
- Kitchens
- Basements
- Laboratories
- Back of house areas

CHARACTERISTICS / ADVANTAGES

- High mechanical resistance
- Good chemical resistance
- Glossy and scratch resistance surface
- Extremely low dirt pick up
- Easy clean and maintain
- Seamless
- Non-tainting, odourless during application
- VOC free and environmental friendly
- Tolerant to moisture in the substrate

- Very good life cycle cost performance

ENVIRONMENTAL INFORMATION

- Conforms to AgBB (2012) for use in indoor environment. Test report No. 392-2014-00156701C. Eurofins Product Testing.


APPROVALS / STANDARDS

- Declaration of CE conformity according to requirements of EN 13813:2002, Declaration of Performance and provided with the CE marking
- Certificate of Compliance to be used safely as a floor coating in food sector. Short term contact of the coating with the foodstuff is safe as far as any hygienic regulations are not violated. Report No. 39438U15. ISEGA Forschungs- und Untersuchungs-Gesellschaft mbH.
- Taint potential, Report No. S/REP/134217/2 Campden BRI (Chipping Campden) Ltd.
- Clean Room Suitable Material (Riboflavin test). Test report SI 1501-752, Sikafloor® -260 PurCem®. Fraunhofer Institute for Manufacturing and Engineering and Automation IPA.
- Fire classification report according to EN 13501-1:2007 + A1:2010. Test report No. 15/9284-338 Parte 1. Applus LGAI.

SYSTEM INFORMATION

System Structure

Sikafloor® PurCem® HS-26 Gloss



Layer	Product	Consumption
1. Scratch coat	Sikafloor®-21 PurCem® or Sikafloor®-210 PurCem® or Sikafloor®-260 PurCem®	~1–2 kg/m ²
2. Wear coat	Sikafloor®-260 PurCem®	~1.8 kg/m ² /mm

Consumptions are theoretical and do not include any wastage, additional material need due to porosity, substrate profile etc.

As an optional build up the primers Sikafloor®-155 W/-156/-161 + quartz sand 0.4–0.8 mm fully blinded broadcast, followed by the Sikafloor®-260 PurCem® (scratch coat) can be used. Please refer to the individual Product Data Sheet.

Composition	Water-based polyurethane cement hybrid
Appearance	Smooth, gloss finish
Colour	Beige, Dusty Grey, Grass Green, Maize Yellow, Night Blue, Oxide Red, Pebble Grey, Tele Grey 2
Nominal Thickness	~2–3 mm
Volatile organic compound (VOC) content	Very low content of Volatile Organic Compounds. It fulfils the stringent demands for indoor air quality and low VOC emitting products AFFSET, M1 Gold, AgBB, EMICODE and A+.

TECHNICAL INFORMATION

Shore D Hardness	~80	(ASTM D 2240)						
Resistance to Wearing	AR0.5	(EN 13892-4)						
Resistance to Impact	Class II (>10 N/mm ²)	(ISO 6272)						
Tensile Adhesion Strength	> 2.0 N/mm ²	(EN 1542)						
Reaction to Fire	Bfl-s1	(EN 13501-1)						
Chemical Resistance	Please refer to Sikafloor® PurCem® Gloss chemical resistance guide. Contact Sika technical service for specific information.							
Thermal Resistance	<table border="1"> <thead> <tr> <th>Thickness</th> <th>Thermal Resistance</th> </tr> </thead> <tbody> <tr> <td>~2 mm</td> <td>-5 °C to +60 °C</td> </tr> <tr> <td>~3 mm</td> <td>-10 °C to +60 °C</td> </tr> </tbody> </table>	Thickness	Thermal Resistance	~2 mm	-5 °C to +60 °C	~3 mm	-10 °C to +60 °C	
Thickness	Thermal Resistance							
~2 mm	-5 °C to +60 °C							
~3 mm	-10 °C to +60 °C							
Permeability to Water Vapour	Class II	(EN 1504-2)						

APPLICATION INFORMATION

Product Temperature	+10 °C min / +35 °C max			
Ambient Air Temperature	+10 °C min / +35 °C max			
Relative Air Humidity	80 % max			
Dew Point	Beware of condensation! The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or other disturbance of the surface on the floor finish.			
Substrate Temperature	+10 °C min / +35 °C max			
Substrate Moisture Content	Sikafloor® PurCem® HS-26 Gloss can be installed on substrates with higher moisture content. The substrate needs to be visibly dry and have an adequate pull-off strength min 1.5 N/mm ² . No ponding water. Check for rising moisture.			
Applied Product Ready for Use	Temperature	Foot traffic	Light traffic	Full cure
	+10 °C	~40 hours	~48 hours	~7 days
	+20 °C	~22 hours	~26 hours	~3 days
	+30 °C	~18 hours	~22 hours	~2 days
Note: Times are approximate and will be affected by changing ambient and substrate conditions				

PRODUCT INFORMATION

Packaging	Please refer to the individual Product Data Sheets
Shelf Life	Please refer to the individual Product Data Sheets
Storage Conditions	Please refer to the individual Product Data Sheets

MAINTENANCE

CLEANING

Please refer to the Sikafloor® Cleaning Regime.

FURTHER DOCUMENTS

- Sikafloor® PurCem® Gloss Information Manual
- Sika® Information Manual Mixing and Application of Flooring Systems
- Sika® Information Manual Surface Evaluation & Preparation
- Sikafloor® PurCem® Product Data Sheets

LIMITATIONS

- Do not apply to PCC (polymer modified cement mortars) that may expand due to moisture when sealed

with an impervious resin.

- Always ensure good ventilation when using Sikafloor® PurCem® products in a confined space, to prevent excessive ambient humidity.
- Freshly applied Sikafloor® PurCem® products, must be protected from damp, condensation and direct water contact (rain) for at least 24 hours.
- Protect the substrate during application from condensation from pipes or any overhead leaks.
- Do not apply to cracked or unsound substrates.
- Always allow a minimum of 48 hours after product application prior to placing into service in proximity with food stuffs.
- Products of the Sikafloor® PurCem® range are subject to discolouration when exposed to UV radiation. Depending on colour there are no measurable losses of any properties when this occurs, and it is a purely aesthetic matter.
- Products can be used outside provided the change in appearance is acceptable for the customer.

- In some slow curing conditions, soiling of the surface may occur when opened to foot traffic, even though mechanical properties have been achieved. It is advised to remove dirt using a dry mop or cloth.
- Avoid scrubbing with water for the first three days.

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

Local safety regulations must be observed and it advisable to wear PPI when working with this product with particular attention paid to cutting and handling. Transportation Class: The product is not classified as hazardous good for transport. Disposal: The material is recyclable. Disposal must be according to local regulations. Please contact your local Sika sales organisation for more information.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @Sikalreland



System Data Sheet

Sikafloor® PurCem® HS-26 Gloss
November 2019, Version 01.01
02081490000000018

SikafloorPurCemHS-26Gloss-en-IE-(11-2019)-1-1.pdf

