

PRODUCT DATA SHEET

SikaCeram[®] FlowFix Jointing Compound

Flowable Porcelain Jointing Compound.

PRODUCT DESCRIPTION

SikaCeram[®] FlowFix Jointing Compound is a ready to use (just add water), flowable joint filling and grouting compound. It is fast to use and delivers exceptional bond strength - perfect for grouting large areas with joints 3-10 mm wide.

USES

- For use with porcelain and ceramic paving.
- Simple and fast application - ideal for large scale areas.
- Suitable for joints 3-10 mm wide and at least 15 mm deep.

CHARACTERISTICS / ADVANTAGES

- Fast setting with exceptional bond strength.
- Simply squeegee into joints for fast and effective application.
- Cures in 60 minutes to a non-permeable finish.
- Suitable for vehicular traffic.
- Can be applied to wet surfaces.
- Exterior use only.

PRODUCT INFORMATION

Packaging	15 kg Buckets (contains 3 x 5 kg bags).
Appearance / Colour	Light Grey / Ivory / Buff / Dark Grey Powder
Shelf Life	If kept accordingly, fully sealed and enclosed in its original container in dry conditions, shelf life will be maximum 9 months from date of manufacture.
Storage Conditions	Protect from frost and store between +5 °C and +20 °C.
Density	Wet density: 2.21 g/cm ³
Compressive Strength	Light Grey: 47.5 MPa Ivory: 62.4 MPa Dark Grey: 37.2 MPa Buff: 37.2 MPa
Flexural Strength	8.1 MPa
Joint width	3-10 mm wide. Minimum 15 mm deep.

APPLICATION INFORMATION

Mixing Ratio	5 kg powder to 0.75 - 0.85 L clean water.
---------------------	-------------------------------------------

Yield	Each 5 kg bag when correctly mixed with water will cover up to 10 m ² based on 600 mm x 600 mm pavers 5 mm wide and 20 mm deep.
Ambient Air Temperature	Between +5 °C and +25 °C.
Pot Life	~20 minutes

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

- Only apply when surface and air temperature is between +5 to +25 °C.
- Do not apply in heavy rain or if heavy rain is likely within 3 hours.
- Do not add further water to the product once mixed.
- Do not try to reconstitute.
- Avoid brushing joints within 24 hours of application to avoid a poor finish.
- Not recommended for use on natural stone and other porous substrates.

ECOLOGY, HEALTH AND SAFETY

Local safety regulations must be observed and it advisable to wear PPI when working with this product with particular attention paid to cutting and handling. Transportation Class: The product is not classified as hazardous good for transport. Disposal: The material is recyclable. Disposal must be according to local regulations. Please contact your local Sika sales organisation for more information.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

- For best results we recommend using **SikaCeram® Flowfix Bonding Primer** to adhere the tiles to the bedding mortar.
- The tiled area must be full set, stable and secure.
- Ensure the substrate is sound, clean and dust free.
- Prior to using the products, ensure the substrate is free from weeds, dirt and organic growth.
- The joints must be clear of material.
- Pre-wet the tiles but ensure there is no standing water.
- The joints must be between 3-10 mm wide with a depth of at least 15 mm.

MIXING

- Mix contents of the bag with clean water as recommended using a drill and spiral action mixer.
- Always add powder to water. Mix for approx. 3 minutes until a smooth, lump free flowable mortar results.
- Do not overmix or create excessive air bubbles within the product.
- Do not mix more product than can be used within 20 minutes.

APPLICATION

- Pour SikaCeram® FlowFix Jointing Compound into the joints immediately after mixing.
- Using a squeegee, work SikaCeram® FlowFix Jointing Compound across the tiled area ensuring all joints are filled.
- Add more product to the joints as required.
- Ensure product has hardened sufficiently in the joints before cleaning the tile faces. This usually takes between 30-60 minutes depending on site conditions.
- Remove any product residue from the tiled surface using a sponge float with clean fresh water.
- Any tough areas should be scrubbed with a stiff brush then washed away once the mortar has begun to cure.
- Do not brush directly over joints.
- Once the mortar has sufficiently set, the tiled area can be polished using a dry soft cloth to remove any final mortar residues.
- Ensure there is no residue of product left on the tiled surface as this will be difficult to remove once set.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @Sikalreland



Product Data Sheet
SikaCeram® FlowFix Jointing Compound
May 2026, Version 01.01
021720100000247909

SikaCeramFlowFixJointingCompound-en-IE-(05-2026)-1-1.pdf

