

PRODUCT DATA SHEET

SikaShield® HB79 Tex 4 mm

Hybrid bituminous membrane surfaced with texflamina and flexible at -25 °C

PRODUCT DESCRIPTION

SikaShield® HB79 Tex 4 mm is an SBS and APAO modified bituminous roof waterproofing membrane with a thickness of 4 mm. The upper layer is APAO modified, which provides good heat resistance, the under layer is SBS modified, increasing the elongation and cold flexibility properties. It is reinforced with a dimensionally stable composite inlay of a fiberglass matt compressed between two layers of non-woven spunbond polyetser fabric and is flexible at -25 °C. The top surface is coated with texflamina, a propylene non-woven fleece.

USES

The Product is used as a waterproofing membrane for:

- Cap sheet for Inverted roof applications
- Flat or sloping roofs with up to 15 % gradient

PRODUCT INFORMATION

Chemical Base	Composition	SBS and APAO modified bitumen	
	Reinforcing material	Composite inlay of a fibreglass matt compressed between two layers of non-woven spunbond polyester fabric	
Packaging	Roll width	1 m	(EN 1848-1)
	Roll length	8.0 m	
Refer to current price list for packaging variations.			
Shelf Life	36 months from date of production		

CHARACTERISTICS / ADVANTAGES

- Combines the advantages of APAO and SBS bitumen
- Easy to install by torching method
- Highly flexible in cold temperatures
- Fully bonded
- High durability
- High heat resistance

APPROVALS / STANDARDS

- UKCA marking and declaration of performance based on EN 13707:2004+A2:2009 Flexible sheets for waterproofing — Reinforced bitumen sheets for roof waterproofing — Definitions and characteristics
- BBA Certified (19/5716)

Storage Conditions

The Product must be stored in original unopened and undamaged packaging in dry conditions and temperatures between +5 °C and +35 °C. Store in a vertical position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.

Appearance / Colour	Top surface	Texflamina, propylene non-woven fleece	
	Bottom surface	Polyethylene film	
	Top layer colour	Refer to current price list for color variations	
Effective Thickness	Effective thickness	4.0 mm ± 0.2 mm	(EN 1849-1)

TECHNICAL INFORMATION

Maximum tensile force	Longitudinal (MD)	750 N/50 mm ± 150 N/50 mm	(EN 12311-1)
	Transversal (CMD)	650 N/50 mm ± 130 N/50 mm	
Elongation at maximum tensile force	Longitudinal (MD)	50 % ± 15 %	(EN 12311-1)
	Transversal (CMD)	50 % ± 15 %	
Resistance to Tearing (nail shank)	Longitudinal (MD)	250 N ± 75 N	(EN 12310-1)
	Transversal (CMD)	250 N ± 75 N	
Joint Shear Resistance	Longitudinal	650 N/50 mm ± 130 N/50 mm	(EN 12317-1)
	Transversal	550 N/50 mm ± 110 N/50 mm	
Flexibility at low temperature	≤ -25 °C		(EN 1109)
Flow resistance	90 °C ± 10 °C		(EN 1110)
Water Tightness	Method B, 24 hours at 60 kPa	Pass	(EN 1928)
Reaction to Fire	Class E		(EN 13501-1)

APPLICATION INFORMATION

Ambient Air Temperature	Minimum	+5 °C
	Maximum	+40 °C
Relative Air Humidity	Maximum	80 %
Substrate Temperature	Minimum	+5 °C
	Maximum	+40 °C

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

- Guidelines and good practice for torch-applied membranes
- Method Statement - Roofing Build-up with Bituminous Membranes

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH: This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w).

APPLICATION INSTRUCTIONS

Please refer to the SikaShield® Installation Guide

MAINTENANCE

Check the functionality of the auxiliary works, flashings, drainage outlets, overflow pipes etc. Remove any leaves, moss and other vegetation, which could cause ponding on the roof and overload the drainage system. To maintain the function of the roof waterproofing membrane during its lifespan, it is advisable to arrange periodically for inspection of the membrane and detailing.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @Sikalreland



Product Data Sheet
SikaShield® HB79 Tex 4 mm
December 2022, Version 03.01
020920011990001670

SikaShieldHB79Tex4mm-en-IE-(12-2022)-3-1.pdf

