

PRODUCT DATA SHEET

Sika® Galvashield Embedding Mortar

LOW RESISTIVITY MORTAR FOR SIKA® GALVASHIELD® ANODES

PRODUCT DESCRIPTION

Sika® Galvashield® Embedding Mortar is a controlled resistivity mortar for use with Sika® Galvashield® discrete corrosion protection anodes. The mortar is designed to provide a low resistance environment around the anode and improved performance.

USES

- Embedding Sika Sika® Galvashield® anodes in vertical and horizontal situations
- To fill grooves which contain anode wires

CHARACTERISTICS / ADVANTAGES

- Easy to use, just add water
- Controlled resistivity mortar
- Portland cement based
- High pH mortar with reservoir of alkali to resist acid generation at the anode

PRODUCT INFORMATION

Chemical Base	Portland cement, selected aggregates and additives
Packaging	20 kg bag
Appearance / Colour	Grey powder
Shelf Life	12 months
Storage Conditions	Store properly in original unopened, sealed and undamaged packaging in dry and cool conditions.

TECHNICAL INFORMATION

Compressive Strength	>50 MPa
Electrical Resistivity	5.0 (kohm.cm)

APPLICATION INFORMATION

Consumption	A 20kg bag will be sufficient for 40 - 80 anodes depending on anode size and mortar thickness.
Ambient Air Temperature	+5°C min. / +30°C max.
Substrate Temperature	+5°C min. / +30°C max.
Pot Life	~ 20-30 minutes (at +23°C)

APPLICATION INSTRUCTIONS

MIXING

Sika® Galvashield® Embedding Mortar should be mixed with a slow speed drill (400/500 rpm) and paddle. Suggested mixing: add up to 3.2 – 3.8 litres of water to each 20kg bag of Sika® Galvashield® Embedding Mortar. Water can be added or deleted to achieve grout consistency desired for placement. Mix for three minutes until fully homogeneous. Mix only as much grout as can be installed in 20-30 minutes.

APPLICATION

Any remaining water should be blown from the drilled hole using oil free compressed air and Sika® Galvashield® Embedding Mortar injected by hand pump to the rear of the hole to avoid air entrapment. Ensure sufficient grout is placed in the bottom of the hole to completely embed the entire active length of the Sika® Galvashield® discrete anode.

The thixotropic nature of the Sika® Galvashield® Embedding Mortar will prevent significant flow from vertical and overhead holes.

Place Sika® Galvashield® Embedding Mortar within 30 minutes of mixing to gain benefit of the expansion system and allow to cure for a minimum of 24 hours, without physical disturbance.

CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened/cured material can only be mechanically removed.

LIMITATIONS

- Avoid application in direct sun and/or strong wind and/or rain.
- Do not add water over recommended dosage.
- Protect freshly applied material from freezing.

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @Sikalreland



Product Data Sheet
Sika® Galvashield Embedding Mortar
June 2019, Version 01.01
020303090030000001

SikaGalvashieldEmbeddingMortar-en-IE-(06-2019)-1-1.pdf

