

PRODUCT DATA SHEET

Sika ViscoFlow®-3000

HIGH RANGE WATER REDUCING/SUPERPLASTICISING CONCRETE ADMIXTURE WITH FAST ABSORPTION CHARACTERISTICS

PRODUCT DESCRIPTION

Sika ViscoFlow®-3000is a liquid admixture for concrete based on unique polycarboxylate polymers technologies. Sika ViscoFlow®-3000 is designed as a high range water reducer or superplasticiser. It is particularly suited for use in concretes that require low water/cement ratios and / or high water reductions. The product provides fast adsorption resulting in highly efficient dispersion and potential reduction in mixing time.

Sika ViscoFlow®-3000 meets the requirements of BS EN 934-2 table.

USES

- Sika ViscoFlow®-3000 is a unique product that is suitable for the production of ready mixed concrete
- Ideally suited for use in SCC and flowing concretes
- Suitability for use across broad range of consistence classes from S3 – SF3
- High performance concrete
- High rise/pumped concrete
- Slip form concrete
- Improved effectiveness in higher ambient temperatures

CHARACTERISTICS / ADVANTAGES

- High range water reductions resulting in higher strengths and densities
- Improved mixing times
- Improved cohesion properties
- Improved early and ultimate strengths
- Excellent placement characteristics
- Improved rheology
- Improved durability
- Reduced segregation and bleeding
- Reduced drying shrinkage
- Reduced mix costs

APPROVALS / STANDARDS

Conforms to the requirements of BS EN 934-2 Tables $3.1 \ \& \ 3.2$

DoP 02 13 01 01 100 0 001346 1088, certified by Factory Production Control Body 0086, Certificate 541325, and provided with the CE mark

PRODUCT INFORMATION

Chemical Base	Modified polycarboxylate
Packaging	20 litre drum, 1000 litre IBC
Appearance / Colour	Light straw
Shelf Life	12 months from date of production if stored properly in undamaged containers.
Storage Conditions	Store in dry conditions at temperatures between +5°C and +25°C. Protect from direct sunlight and frost.
Density	1.05 kg/l (at +20°C)

Product Data Sheet Sika ViscoFlow®-3000 June 2019, Version 01.01 021301011000001524

pH-Value	5.0 +/- 1.0
Total Chloride Ion Content	<0.1% w/w (chloride free)

TECHNICAL INFORMATION

Specific Advice	Alkali Content: <0.35% w/w
	Freezing Point: +1°C
	Air Entrainment: Negligible, minimal increase
	Effect of Setting: Minimal effect
	Effect of Overdosing: Increased workability and segregation

APPLICATION INFORMATION

Recommended Dosage	0.5 - 1.5% by weight of cement
Compatibility	Sika ViscoFlow®-3000 may be combined with many other Sika products. Important: Always conduct trials before combining products in specific mixes and contact our Technical Service Department for information and advice about any specific combinations.
Dispensing	Sika ViscoFlow®-3000 should be dispensed through suitable calibrated dosing equipment. Sika ViscoFlow®-3000 is added to the gauging water or added with it into the concrete mixer.

APPLICATION INSTRUCTIONS

Application Method / Tools

- The standard rules of good concreting practice, concerning production and placing, are to be followed.
- Laboratory trials shall be carried out before concreting on site, especially when using a new mix design or producing new concrete components.
- Fresh concrete must be cured properly and curing applied as soon as possible.

Notes on Application / Limitations

- When using Sika ViscoFlow®-3000 a suitable mix design has to be taken into account and local material sources shall be trialled.
- Sika ViscoFlow®-3000 shall not be added to dry cement
- Excessive water addition or overdosing may cause bleeding or segregation.
- Support from our Technical Service Department is recommended.

Frost:

If frozen and / or if precipitation has occurred, Sika ViscoFlow®-3000 may be used after thawing slowly at room temperature followed by intensive remixing.

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local

Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

Local safety regulations must be observed and it advisable to wear PPI when working with this product with particular attention paid to cutting and handling. Transportation Class: The product is not classified as hazardous good for transport. Disposal: The material is recyclable. Disposal must be according to local regulations. Please contact your local Sika sales organisation for more information.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



SIKA IRELAND LIMITED

Ballymun Industrial Estate Ballymun Dublin 11, Ireland Tel: +353 1 862 0709 Web: www.sika.ie Twitter: @Sikalreland



Product Data Sheet Sika ViscoFlow®-3000 June 2019, Version 01.01 021301011000001524 SikaViscoFlow-3000-en-IE-(06-2019)-1-1.pdf

