

# PRODUCT DATA SHEET

## Sikagard®-406 W

### SINGLE COMPONENT, WATERBORNE ACRYLIC RESIN WALL COATING

#### PRODUCT DESCRIPTION

Sikagard®-406 W is a single component white, water-borne acrylic resin based surface coating containing an organic in film preservative with a mat finish.

#### USES

Sikagard®-406 W installation works to be carried out only by Sika Approved Contractors. Please observe information given by Product Data Sheets.

- Top coat or standalone coating for internal walls and ceilings
- For concrete, bricks, cement based and gypsum substrates, metallic surfaces, timber, tiles and plastic
- Suitable for pharmaceutical, medical engineering, food and beverage industry, hospitals, healthcare facilities, kitchens and prisons and leisure facilities

#### CHARACTERISTICS / ADVANTAGES

- Easy to apply
- Good resistance to repeated cleaning regimes using mild detergents and cleaning solutions
- Tough and highly durable
- Good covering and hiding power (opacity)
- Permeable to water vapour
- Ultra-low emission
- More flexible in comparison to standard paints, improved resistance to cracking and flaking
- Mat finish
- Seamless, easy to clean finish
- Low odour

#### ENVIRONMENTAL INFORMATION

##### LEED Rating

Sikagard®-406 W conforms to the requirements of LEED EQ Credit 4.2: Low –Emitting Materials: Paints & Coatings SCAQMD Method 304-91 VOC Content < 100 g/l

#### APPROVALS / STANDARDS

- Exova Warrington fire, test report No. 363981 & 363982, behaviour to fire according to BS 476, April 27, 2016
- Eurofins, test report No. 392-2015-00386902, determination of VOC and SVOC content according to ISO 11890-2/ ASTM D6886, December 10, 2015
- PRA, test report No. 77564-049, gloss, fineness, grind wet scrub resistance and contrast ratio according to EN 13300, November 21, 2015.
- IMSL, test report 2015/02/004.1A, determination of antibacterial activity according to ISO 22196, May 12, 2015
- Campden BRI Group, test report No. S/REP/138532/2, Sensory Evaluation of the Taint Potential, Triangle Test Method TES-S-002 according to EN ISO 4120:2007, Odour Transfer Method, February 8, 2016
- TÜV Rheinland, test report 21246824001, determination of VOC emission according to French Regulations Decret DEVL 1101903D and Decret DEVL 11034675A, November 18, 2015
- 4wardtesting, test report No. C 2906, water vapour permeability according to ISO 7783-1:2000, January 5, 2016

## PRODUCT INFORMATION

<b>Chemical Base</b>	Waterborne acrylic copolymer dispersion		
<b>Packaging</b>	5.0 l (= 6.60kg) drums 15.0 l (= 19.80 kg) containers		
<b>Appearance / Colour</b>	White, mid-sheen		
<b>Shelf Life</b>	12 month from date of production		
<b>Storage Conditions</b>	From date of production if stored properly in closed, sealed undamaged packaging in dry conditions at temperatures between +5°C and +30°C. Protect from direct sunlight and frost.		
<b>Density</b>	~1.24 kg/l		(DIN EN ISO 2811-1)
<b>Solid content by weight</b>	~52 %		
<b>Solid content by volume</b>	~40 %		

## TECHNICAL INFORMATION

<b>Tensile Strength</b>	~10 N/mm <sup>2</sup> unreinforced		(EN ISO 527-3)
<b>Elongation at Break</b>	~70 % unreinforced		(EN ISO 527-3)
<b>Tensile Adhesion Strength</b>	≥ 1.5N/mm <sup>2</sup>	to concrete using Sika Bonding Primer	(ISO 4624)

### Chemical Resistance

Good short-term resistance to weak acids, alkalis and cleaning products. Please contact Sika technical service for specific information.

Disinfection with Hydrogen Peroxide Vapour:

- Resistant when using Steris VHP technology
- Resistant to PEA vaporisation technology, when a system build up with glass fibre reinforcement is used
- Resistant when using Oxypharm vaporiser type Nocospray under following conditions:

Disinfectant	Concentration	Setting at vaporiser	Contact time
NOCOLYSE Mint (6 %)	1 ml/m <sup>3</sup>	20 m <sup>3</sup> (1.5 minutes vaporisation)	30 min
NOCOLYSE One Shot (12 %)	3 ml/m <sup>3</sup> (2 cycles)	45m <sup>3</sup> (5 minutes vaporisation)	30 min
NOCOLYSE Food (7.9 %)	1 ml/m <sup>3</sup>	20 m <sup>3</sup> (1.5 minutes vaporisation)	30 min
NOCOLYSE Food (7.9 %)	5 ml/m <sup>3</sup> (2 cycles)	75m <sup>3</sup> (5 minutes vaporisation)	60 min

## APPLICATION INFORMATION

<b>Consumption</b>	~0.23kg/m <sup>2</sup> per layer ~0.18 l/m <sup>2</sup> per layer
<b>Ambient Air Temperature</b>	+8°C min. / +35°C max.
<b>Relative Air Humidity</b>	≤ 80%
<b>Dew Point</b>	Beware of condensation! The substrate must be at least 3 °C above dew point to reduce the risk of condensation or blooming on the wall finish.
<b>Substrate Temperature</b>	+8 °C min. / +35 °C max.

**Substrate Moisture Content**

Visible damp free, < 6 % pbw moisture content test method: Sika®-Tramex meter

**Curing Time**

Before applying Sikagard®-406 W to Sikagard®-406 W allow:

Substrate temperature	Minimum	Maximum
+10 °C	4 hours	7 days
+20 °C	2 hours	7 days
+30 °C	1 hour	7 days

Before applying Sikagard®-406 W to Sikagard®-403 W allow:

Substrate temperature	Minimum	Maximum
+10 °C	4 hours	7 days
+20 °C	1 hour	7 days
+30 °C	1 hour	7 days

**Applied Product Ready for Use**

Temperature	Tack free	Full cure
+10 °C/ 50 % r.h.	~ 8 hours	~ 7days
+20 °C/ 50 % r.h.	~ 4 hours	~ 7days
+30 °C/ 50 % r.h.	~ 3 hours	~ 7days

**APPLICATION INSTRUCTIONS****APPLICATION**

Stir product until a uniform liquid is achieved. Use low speed stirrer (300-400 rpm) to avoid air entrapment. For Roller application use short piled roller. For airless application use tip size from 0.38 to 0.53mm and angle from 40° to 60°.

**CLEANING OF TOOLS**

Clean all tools and application tools with water immediately after use. Hardened and/ or cured material can only be removed mechanically or with proprietary paint stripper.

**LIMITATIONS**

- Each method of application will leave a different surface finish. If surface finish is important do not mix methods within single areas.
- Each type of roller will give a slightly different surface finish - always use same roller type in same areas.
- Ensure entire surface is fully dried before proceeding. Cracking may occur over coating un-dried surfaces or when applying excessively thick material.
- Do not apply over silicone sealants.
- Always ensure good ventilation when application takes place in a confined space to ensure drying and full curing.
- The gloss of the applied material is influenced by humidity, temperature and absorbency of the substrate.
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.
- For spray application the use of protective health & safety equipment is mandatory!
- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO<sub>2</sub> and H<sub>2</sub>O water vapour, which may adversely affect the finish. For heating use only elec-

tric powered warm air blower systems.

- New concrete should be allowed to cure/hydrate for a minimum of 10 days and preferably 28 days.
- Do not apply near foodstuffs in unventilated conditions, always ensure adequate ventilation.
- Do not thin or brush out like conventional paints.
- Acoustic insulation boards may lose some acoustic absorption after coating.

**VALUE BASE**

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

**LOCAL RESTRICTIONS**

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

**ECOLOGY, HEALTH AND SAFETY**

Local safety regulations must be observed and it advisable to wear PPI when working with this product with particular attention paid to cutting and handling. Transportation Class: The product is not classified as hazardous good for transport. Disposal: The material is recyclable. Disposal must be according to local regulations. Please contact your local Sika sales organisation for more information.

**DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC**

According to the EU-Directive 2004/42, the maximum allowed content of VOC (Product category IIA / j type wb) is 140 g/l (Limits 2010) for the ready to use product. The maximum content of Sikagard®-406 W W is <140 g/l VOC for the ready to use product.



## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA IRELAND LIMITED

Ballymun Industrial Estate  
Ballymun  
Dublin 11, Ireland  
Tel: +353 1 862 0709  
Web: [www.sika.ie](http://www.sika.ie)  
Twitter: @Sikalreland



Product Data Sheet  
Sikagard®-406 W  
June 2019, Version 02.01  
020813020020000024

Sikagard-406W-en-IE-(06-2019)-2-1.pdf

